Heraeus

Technical Data Sheet



ASSEMBLY MATERIALS

Product Type: No Clean Solder PasteProduct Name: F645 SAC305-89M40

Description

F645 SAC305-89M40 solder paste is a state-ofthe-art halogen-free lead free no clean solder paste that promotes wetting and minimises soldering defects. Extensive testing at customer locations has proven this paste to be capable of defect-free performance in the production environment.

Key Benefits

- Exceptional print to print consistency
- Outstanding wetting

Compliant Products

- Flux SF 64
- Applications
- Printing


Product Code and Alloy

Product Code					Powder Properties		
Paste	Alloy	Metal Content	*Viscosity	Powder Type	Particle Size	Alloy	Melting Point
F645	SAC305	89%	М	4	20 – 38 µm	Sn96.5/Ag3/Cu0.5	217 °C
*D - Diananaa grada M - Drint grada H - Drint grada high I - Dianing/latting grada law							

D = Dispense grade M = Print grade H = Print grade, high L = Dipping/Jetting grade, Low

Flux Activity							
Activity Level (J-STD 004)	ISO 9454-1 {DIN EN 29454-1}	Classification					
RELO	1.2.3.C	No Clean/ Solvent Clean					





* Graph not drawn to scale

Halogen Content Halogen-Zero (No halogen added in the flux)

Tolerances: Halogen < 50 ppm; measured according to BS EN 14582

Recommended Profile					
Average Ramp Rate	1 – 3 °C/s				
	15 °C (min) –				
Peak Temperature	40 °C (max)				
	above Melting				
	Temperature				
Time above liquidus	45 – 90 s				
Reflow Atmosphere	Reflow in Air				
	or in N ₂ with				
Туре 3 – 5	< 2000 ppm 0 ₂				

The descriptions and engineering data shown here have been compiled by Heraeus using commonly-accepted procedures, in conjunction with modern testing equipment, and have been compiled as according to the latest factual knowledge in our possession. The information was up-to date on the date this document was printed (latest versions can always be supplied upon request). Although the data is considered accurate, we cannot guarantee accuracy, the results obtained from its use, or any patent infringement resulting from its use (unless this is contractually and explicitly agreed in writing, in advance). The data is supplied on the condition that the user shall conduct tests to determine materials suitability for a particular application)

Heraeus

Technical Data Sheet

Cleaning Instructions

After reflow flux residues may remain on the circuit and do not need to be washed. For cleaning of wet paste or if desired for cleaning of flux residues Zestron and Vigon cleaners can be used – see separate cleaning

Storage

- Store the solder paste in tightly-sealed containers and avoid exposure to sunlight and high humidity
- Max expiration date: please refer to the expiry date on the label of the packaged product
- Storage condition in the refrigerator at 2 -10 °C
- Store cartridges with tip pointing downwards

Paste Preparation

- Remove paste from fridge: Before opening the package, leave paste for at least 4 hours (depending on jar/ cartridge size) at room temperature, so that paste warms up
- Do not open jar/cartridge while paste is cold to prevent condensation
- Do not heat the paste beyond room temperature
- Before using of paste jar: To obtain uniform, stable viscosity stir paste for 1 to 2 min, using a stainless steel or chemically resistive plastic spatula
- For further information see Technical Information

Heraeus Electronics

Heraeus Deutschland GmbH & Co. KG Heraeusstraße 12 – 14 63450 Hanau, Germany www.heraeus-electronics.com

Americas

Phone +1 610 825 6050 electronics.americas@heraeus.com

Asia Pacific

Phone +65 6571 7677 electronics.apac@heraeus.com

China

Phone +86 21 3357 5457 electronics.china@heraeus.com

Europe, Middle East and Africa

Phone +49 6181 35 3069, +49 6181 35 3627 electronics.emea@heraeus.com

The descriptions and engineering data shown here have been compiled by Heraeus using commonly-accepted procedures, in conjunction with modern testing equipment, and have been compiled as according to the latest factual knowledge in our possession. The information was up-to date on the date this document was printed (latest versions can always be supplied upon request). Although the data is considered accurate, we cannot guarantee accuracy, the results obtained from its use, any patent infingement resulting from its use (unless this is constructually and explicitly agreed in writing, in advance). The data is supplied on the condition that the user shall conduct tests to determine materials suitability for particular applications.