

MOLYKOTE® HTP Paste

Solid lubricating paste for hot forming of metals

Features

- High-temperature resistance (up to 1,150°C)
- Reduces friction and wear
- Reduces scoring
- Increases service life of tools

Composition

- Mineral oil
- Thickener
- Solid lubricant

Applications

Suitable for the lubrication of tools for hot forming, particularly on hot-flow presses and drop forging; also as a parting agent and slip additive at high temperatures. Used successfully for the hot bending of flat steel St 37 or St 70, the rolling of the ends of vehicle leaf-springs, folding of sheet metal edges, hot rolling of cutters, and drop forging of flywheels made from St 37, as well as for the lubrication of separator plates on chipboard presses.

How to use

Apply MOLYKOTE® HTP Paste with a suitable brush or a rag, thinly and uniformly to the cleaned workpiece or tool. Application should be repeated from time to time, as required.

Handling precautions

PRODUCT SAFETY INFORMATION REQUIRED FOR SAFE USE IS NOT INCLUDED IN THIS DOCUMENT. BEFORE HANDLING, READ SAFETY DATA SHEETS AND CONTAINER LABELS FOR SAFE USE, PHYSICAL AND HEALTH HAZARD INFORMATION.

Usable life and storage

When stored at or below 20°C in the original unopened containers, this product has a usable life of 60 months from the date of production.

Packaging

This product is available in different standard container sizes. Detailed container size information should be obtained from your nearest MOLYKOTE® sales office or MOLYKOTE® distributor.

Typical properties

Specification writers: These values are not intended for use in preparing specifications. Please contact your local MOLYKOTE® sales representative prior to writing specifications on this product.

Standard ⁽¹⁾	Test	Unit	Result
	Color		White
Penetration, density, viscosity			
ISO 2137	Unworked penetration	mm/10	250-280
ISO 2811	Density at 20°C	g/ml	1.5
Temperature			
	Service temperature ⁽²⁾	°C	-20 to +1,150
Load-carrying capacity, wear protection, service life			
	Four-ball tester (VKA)		
DIN 51 350 pt.4	Weld load	N	2,200
DIN 51 350 pt.5	Wear scar under 800 N load	mm	1.0
	Almen-Wieland machine		
	OK load	N	20,000
	Friction force	N	2,300

⁽¹⁾ISO: International Standardization Organization. DIN: Deutsche Industrie Norm.

⁽²⁾Temperature resistance of solid lubricants.

DuPont™, the DuPont Oval Logo, and all trademarks and service marks denoted with ™, SM or ® are owned by affiliates of DuPont de Nemours, Inc. unless otherwise noted.
© 1997-2020 DuPont.

The information set forth herein is furnished free of charge and is based on technical data that DuPont believes to be reliable and falls within the normal range of properties. It is intended for use by persons having technical skill, at their own discretion and risk. This data should not be used to establish specification limits nor used alone as the basis of design. Handling precaution information is given with the understanding that those using it will satisfy themselves that their particular conditions of use present no health or safety hazards. Since conditions of product use and disposal are outside our control, we make no warranties, express or implied, and assume no liability in connection with any use of this information. As with any product, evaluation under end use conditions prior to specification is essential. Nothing herein is to be taken as a license to operate or a recommendation to infringe on patents.