

PERMABOND® UV686.21

UV-Cure Gasketmaker
Provisional Technical Datasheet

Features & Benefits

- Flexible form-in-place gasket
- Silicone & isocyanate free
- Excellent environmental resistance
- 100% solids, no solvents
- Dual cure mechanism UV and heat
- UV and Visible light cure

Description

PERMABOND® UV686.21 is a UV-curable adhesive designed for making FIP (form-in-place) gaskets. It can be used to form flexible joints and can be deformed and compressed (it has good internal cohesion and elasticity). It is suitable for use on large panels and will cure in gaps of up to 0.2mm.It can be used as a flexible barrier/sealant in combination with metals, ceramics and plastics in electronic devices. Cure wavelengths are typically 365 – 400 nm)

Physical Properties of Uncured Adhesive

Chemical composition	Urethane acrylate
Appearance	Clear
Viscosity @ 25°C	1000-3000mPa s (cP)
Specific Gravity	1.1

ypical Curing Properties

Fixture time (3 / 5 mW/sqcm)*	10-30 seconds
Fixture time (at +115°C on metal)	10-15 minutes


^{*}The cure time depends on the power of the UV lamp, its spectral output, the distance between the lamp and the components, and the transmission characteristics of the substrates. The cure time quoted here was determined using a low power, hand held lamp. Most industrial UV lamps would give faster cure rate.

Typical Performance of Cured Adhesive

Tensile strength DIN 53504*	3-6 N/mm² (450-900 psi)
Shore Hardness ISO868	15-25 Shore A
Elongation at break DIN 53504	200-400%
Light Transmittance	>99%

^{*}Strength results will vary depending on the level of surface preparation and gap.

Temperature Resistance



Temperature °C

UV686.21 can withstand higher temperatures for brief periods (such as for paint baking and wave soldering processes) providing the joint is not unduly stressed. The minimum temperature the cured adhesive can be exposed to is -55°C (-67°F) depending on the materials being bonded.

The information given and the recommendations made herein are based on our research and are believed to be accurate but no guarantee of their accuracy is made. In every case we urge and recommend that purchasers before using any product in full-scale production make their own tests to determine to their own satisfaction whether the product is of acceptable quality and is suitable for their particular purpose under their own operating conditions. THE PRODUCTS DISCLOSED HEREIN ARE SOLD WITHOUT ANY WARRANTY AS TO MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE OR ANY OTHER WARRANTY, EXPRESS OR IMPLIED.

No representative of ours has any authority to waive or change the foregoing provisions but, subject to such provisions, our engineers are available to assist purchasers in adapting our products to their needs and to the circumstances prevailing in their business. Nothing contained herein shall be construed to imply the non-existence of any relevant patents or to constitute a permission, inducement or recommendation to practice any invention covered by any patent, without authority from the owner of this patent. We also expect purchasers to use our products in accordance with the guiding principles of the Chemical Manufacturers Association's Responsible Care® program.

Additional Information

This product is not recommended for use in contact with strong oxidizing materials.

Information regarding the safe handling of this material may be obtained from the material safety data sheet (MSDS).

Users are reminded that all materials, whether innocuous or not, should be handled in accordance with the principles of good industrial hygiene.

Surface Preparation

Surfaces should be clean, dry and grease-free before applying the adhesive. Particular care should be taken to remove silicone based cleaning agents which may have been used previously to clean glass.

Some metals such as aluminium, copper and its alloys, will benefit from light abrasion with emery cloth (or similar) to remove the oxide layer.

Isopropanol can be used to degrease most surfaces. Where thermoplastic surfaces are involved we recommend tests are done to ensure compatibility, mold release agents may affect bond strength.

Directions for Use

- Adhesive can either be applied directly from the bottle or dispensed via automated dispensing equipment for more accurate dosing.
- 2. Apply the adhesive in a continuous bead taking care to avoid any air entrapment.
- Adhesive can then be cured with a UV lamp. Parts can be assembled as and when desired, the flexibility of the UV gasket will conform to fit between components when clamped together.

Storage & Handling

Storage Temperature	5 to 25°C (41 to 77°F)
Shelf Life Stored in original unopened containers	6 months

Contact Permabond:

Europe: Tel. +44 (0)1962 711661 US: Tel. +1 732-868-1372 UK Helpline: 0800 975 9800 Helpline: 800-640-7599

Deutschland: 0800 10 13 177 info.americas@permabond.com

France: 0805 11 13 88 Asia: Tel. +86 21 5773 4913 info.europe@permabond.com info.asia@permabond.com

www.permabond.com

The information given and the recommendations made herein are based on our research and are believed to be accurate but no guarantee of their accuracy is made. In every case we urge and recommend that purchasers before using any product in full-scale production make their own tests to determine to their own satisfaction whether the product is of acceptable quality and is suitable for their particular purpose under their own operating conditions. THE PRODUCTS DISCLOSED HEREIN ARE SOLD WITHOUT ANY WARRANTY AS TO MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE OR ANY OTHER WARRANTY, EXPRESS OR IMPLIED.

No representative of ours has any authority to waive or change the foregoing provisions but, subject to such provisions, our engineers are available to assist purchasers in adapting our products to their needs and to the circumstances prevailing in their business. Nothing contained herein shall be construed to imply the non-existence of any relevant patents or to constitute a permission, inducement or recommendation to practice any invention covered by any patent, without authority from the owner of this patent. We also expect purchasers to use our products in accordance with the guiding principles of the Chemical Manufacturers Association's Responsible Care® program.