

# MOLYKOTE® YM-103 Grease

Lubricating grease developed for plastic components

## Features

- Compatible with most plastics
- Good load-carrying capability and wear resistance
- Long service life
- Low seepage, so it can be used in places wherein cleanliness is required

## Composition

- Polyalphaolefin
- Lithium soap
- Special solid lubricants

## Applications

Automobiles, electrical appliances, precision equipment, and office equipment. Can be used with plastic-on-plastic, metal-on-metal, or plastic-on-metal friction parts.

## How to use

Clean points of application. As is usual with lubricating greases, apply or fill by means of a brush, spatula, or automatic lubrication device.

## Handling precautions

PRODUCT SAFETY INFORMATION REQUIRED FOR SAFE USE IS NOT INCLUDED IN THIS DOCUMENT. BEFORE HANDLING, READ SAFETY DATA SHEETS AND CONTAINER LABELS FOR SAFE USE, PHYSICAL AND HEALTH HAZARD INFORMATION.

## Usable life and storage

When stored, unopened, in a cool, dark place, this product has a usable life of 36 months from the date of production.

## Packaging

This product is available in 1 kg cans (10 cans/case) and 16 kg pails.

## Typical properties

Specification writers: These values are not intended for use in preparing specifications. Please contact your local MOLYKOTE® sales representative prior to writing specifications on this product.

Standard <sup>(1)</sup>	Test	Unit	Result
	Appearance		Yellow
	Base oil viscosity at 40°C	mm <sup>2</sup> /s	29
JIS K 2220	Penetration (worked 60 times)		300
	NLGI class		1 to 2
	Service temperature range	°C	-45 to 150
	Density	g/cm <sup>3</sup>	0.90
JIS K 2220	Drop point	°C	195
JIS K 2220	Bleed (100°C/24 hours)	%	3.0
JIS K 2220	Evaporation (99°C/22 hours)	%	0.2
JIS K 2220	Oxidation resistance (99°C/100 hours)	MPa	0.02
JIS K 2220	Copper corrosion (100°C/24 hours)		1a
ASTM D2596	Four ball weld load (1,500 rpm/1 minute)	N	5,200
ASTM D2266	Four ball wear scar (1,200 rpm, 392 N, 1 hour)	mm	0.40
JIS K 2220	Low temperature torque test (-40°C)		
	Starting torque	mN.m	93
	Running torque	mN.m	49

<sup>(1)</sup>JIS: Japanese Industrial Standard. ASTM: American Society for Testing and Materials.

*DuPont™, the DuPont Oval Logo, and all trademarks and service marks denoted with ™, SM or ® are owned by affiliates of DuPont de Nemours, Inc. unless otherwise noted.*  
© 2006-2021 DuPont.

The information set forth herein is furnished free of charge and is based on technical data that DuPont believes to be reliable and falls within the normal range of properties. It is intended for use by persons having technical skill, at their own discretion and risk. This data should not be used to establish specification limits nor used alone as the basis of design. Handling precaution information is given with the understanding that those using it will satisfy themselves that their particular conditions of use present no health or safety hazards. Since conditions of product use and disposal are outside our control, we make no warranties, express or implied, and assume no liability in connection with any use of this information. As with any product, evaluation under end use conditions prior to specification is essential. Nothing herein is to be taken as a license to operate or a recommendation to infringe on patents.