

Technical Data Sheet



ASSEMBLY MATERIALS

Product Type: mAgic Ag Sinter Paste

Product Name: ASP 295-79P2

Description

mAgic Sinter Paste ASP 295-79P2 is designed for Die Attach on lead frame application requiring excellent thermal conductivity. The material is lead free and does not contain halogens. It consists of micro scaled Ag powder.

Key Benefits

- No pressure sintering process at temperature of 230 °C
- Typical thermal conductivity of 100 W/mK and above
- Pb and halogen free formulation

Applications

- Dispensing

Product Code

Product Name	Compatible Surfaces	Sintering Atmosphere
ASP 295 – 79P2	Ag	Air / N ₂ [Min. O ₂ > 50 ppm]

Processing

Dispensing to be done using dot dispensing or needle writing system. Recommended inner diameter of dispensing needle for dot dispensing ≥ 0.33 mm, for needle writing ≥ 0.4 mm. Dies ≤ 25 mm² can be sintered without process pressure using the recommended sintering profile. See detailed information on application information sheet. Process parameters need to be adjusted depending on specific application requirements.

Cleaning

The material does not leave undesirable residues after processing. Therefore cleaning is usually not necessary.

Storage

- Store the sinter paste tightly-sealed and avoid exposure to sunlight and high humidity > 65 % R.H
- Max expiration date: please refer to the expiry date on the label of the packaged product
- Storage conditions in the refrigerator at 2 – 10 °C
- Store syringes with tip pointing downwards

Paste Preparation

- Remove material from fridge: Before opening the package leave it at least 2 hours at room temperature so that paste warms up
- Do not open syringe while material is cold to prevent condensation
- Do not use accelerated defrost procedure

Heraeus Electronics
Heraeus Deutschland GmbH & Co. KG
Heraeusstraße 12 – 14
63450 Hanau, Germany
www.heraeus-electronics.com

Americas
Phone +1 610 825 6050
electronics.americas@heraeus.com

Asia Pacific
Phone +65 6571 7677
electronics.apac@heraeus.com

China
Phone +86 21 3357 5457
electronics.china@heraeus.com

Europe, Middle East and Africa
Phone +49 6181 35 3069, +49 6181 35 3627
electronics.emea@heraeus.com

The descriptions and engineering data shown here have been compiled by Heraeus using commonly-accepted procedures, in conjunction with modern testing equipment, and have been compiled as according to the latest factual knowledge in our possession. The information was up-to date on the date this document was printed (latest versions can always be supplied upon request). Although the data is considered accurate, we cannot guarantee accuracy, the results obtained from its use, or any patent infringement resulting from its use (unless this is contractually and explicitly agreed in writing, in advance). The data is supplied on the condition that the user shall conduct tests to determine materials suitability for particular application.