



Technical Data Sheet

SYLGARD™ 517 Dielectric Gel Kit

General purpose silicone gel

Features & Benefits

- Two-part, 1:1 mixing ratio
- Low viscosity
- Room temperature cure or rapid heat cure
- Addition cure system: no cure by-products
- Self-healing gel
- Permanent pressure sensitive adhesion to most materials without use of a primer
- Stable and flexible from -50°C to +200°C
- Clear
- Excellent dielectric properties

Applications

- Designed to provide long term sealing against moisture and atmospheric contaminants.
- Typical applications include: sealing and protection of delicate electronic circuits, hybrid devices and sealing of small appliances.

Typical Properties

Specification Writers: These values are not intended for use in preparing specifications.

CTM ¹	ASTM ²	Property	Unit	Result
As supplied				
0176		Color (part A/part B)		Clear
0050	D1084	Viscosity at 23°C (part A/part B) ³	mPa.s	450/450
Mixed 1:1 by weight or volume				
0050	D1084	Viscosity at 23°C ³	mPa.s	450
0022	D0792	Specific gravity at 23°C		0.97
Physical properties, cured 1 hour at 150°C				
0176		Color (part A/part B)		Clear
		Penetration	mm x 10 ⁻¹	45
Electrical properties, cured 1 hour at 150°C				
0114	D0149	Dielectric strength	kV/mm	15
0249	D257	Volume resistivity	Ohm.cm	3x10 ¹⁵

1. CTM: Corporate Test Method, copies of CTMs are available on request.

2. ASTM: American Society for Testing and Materials.

3. Brookfield LVF, spindle #3 at 60 rpm

How to Use

Substrate Preparation

All surfaces should be cleaned and degreased with a suitable solvent prior to potting. Care should be taken to ensure that all solvent is removed.

Mixing

SYLGARD™ 517 Dielectric Gel Kit is supplied in lot matched kits consisting of Part A and Part B in separate containers.

The two components should be thoroughly mixed using a weight or volume ratio of 1:1.

Vacuum de-airing is recommended. A residual pressure of 1020 mm mercury applied for 5-10 minutes will sufficiently de-air the material.

Pot Life

When the two components are thoroughly mixed in a 1:1 ratio, SYLGARD™ 517 Dielectric Gel Kit will have a working time of about 16 hours at room temperature. The viscosity of the initial mix will double in about 2 hours at room temperature (pot life).

How to Apply

Apply the encapsulant, being careful to avoid air entrapment. Vacuum encapsulation is recommended for complex geometries.

For information on appropriate dispensing equipment for your application, please contact Dow.

Curing

SYLGARD™ 517 Dielectric Gel Kit should be cured using one of the following recommended schedules:

4 hours at 65°C, or 1 hour at 100°C, or 15 minutes at 150°C.

Large components and assemblies may require longer times in order to reach the curing temperature. Considerably shorter cure times can result when the part is pre-heated prior to adding the product or when the product is applied in thin sections.

Compatibility

In some cases, SYLGARD™ 517 Dielectric Gel Kit may fail to cure to optimum properties when in contact with certain plastics or rubbers.

Cleaning the substrate with solvent or baking slightly above the cure temperature can eliminate the problem.

Certain chemicals, curing agents and plasticisers can inhibit cure. These include:

- Organotin compounds
- Silicone rubber containing organotin catalysts
- Sulphur, polysulphides, polysulphones and other sulphur containing materials
- Amines, urethanes, amides and azides

How to Use (Cont.)**Repairability**

When cured in place, SYLGARD™ 517 Dielectric Gel Kit can be removed with relative ease, repairs or changes made and protected with additional gel.

Since this gel develops a good adhesion to itself, the repaired region will become an integral part of the original material.

**Handling
Precautions**

PRODUCT SAFETY INFORMATION REQUIRED FOR SAFE USE IS NOT INCLUDED IN THIS DOCUMENT. BEFORE HANDLING, READ PRODUCT AND SAFETY DATA SHEETS AND CONTAINER LABELS FOR SAFE USE, PHYSICAL AND HEALTH HAZARD INFORMATION. THE SAFETY DATA SHEET IS AVAILABLE ON THE DOW WEBSITE AT DOW.COM, OR FROM YOUR DOW SALES APPLICATION ENGINEER, OR DISTRIBUTOR, OR BY CALLING DOW CUSTOMER SERVICE.

**Usable Life and
Storage**

When stored at or below 35°C in the original unopened containers, this product has a usable life of 12 months from the date of production.

**Packaging
Information**

This product is available in standard industrial container sizes. For details please refer to your Dow sales office.

Limitations

This product is neither tested nor represented as suitable for medical or pharmaceutical uses.

**Health and
Environmental
Information**

To support customers in their product safety needs, Dow has an extensive Product Stewardship organization and a team of product safety and regulatory compliance specialists available in each area.

For further information, please see our website, dow.com or consult your local Dow representative.

**Disposal
Considerations**

Dispose in accordance with all local, state (provincial) and federal regulations. Empty containers may contain hazardous residues. This material and its container must be disposed in a safe and legal manner.

It is the user's responsibility to verify that treatment and disposal procedures comply with local, state (provincial) and federal regulations. Contact your Dow Technical Representative for more information.

**Product
Stewardship**

Dow has a fundamental concern for all who make, distribute, and use its products, and for the environment in which we live. This concern is the basis for our product stewardship philosophy by which we assess the safety, health, and environmental information on our products and then take appropriate steps to protect employee and public health and our environment. The success of our product stewardship program rests with each and every individual involved with Dow products - from the initial concept and research, to manufacture, use, sale, disposal, and recycle of each product.

Customer Notice

Dow strongly encourages its customers to review both their manufacturing processes and their applications of Dow products from the standpoint of human health and environmental quality to ensure that Dow products are not used in ways for which they are not intended or tested. Dow personnel are available to answer your questions and to provide reasonable technical support. Dow product literature, including safety data sheets, should be consulted prior to use of Dow products. Current safety data sheets are available from Dow.

How Can We Help You Today?

Tell us about your performance, design, and manufacturing challenges. Let us put our silicon-based materials expertise, application knowledge, and processing experience to work for you.

For more information about our materials and capabilities, visit **dow.com**.

To discuss how we could work together to meet your specific needs, go to **dow.com** for a contact close to your location. Dow has customer service teams, science and technology centers, application support teams, sales offices, and manufacturing sites around the globe.

dow.com

NOTICE: No freedom from infringement of any patent owned by Dow or others is to be inferred. Because use conditions and applicable laws may differ from one location to another and may change with time, Customer is responsible for determining whether products and the information in this document are appropriate for Customer's use and for ensuring that Customer's workplace and disposal practices are in compliance with applicable laws and other government enactments. The product shown in this literature may not be available for sale and/or available in all geographies where Dow is represented. The claims made may not have been approved for use in all countries. Dow assumes no obligation or liability for the information in this document. References to "Dow" or the "Company" mean the Dow legal entity selling the products to Customer unless otherwise expressly noted. NO WARRANTIES ARE GIVEN; ALL IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE ARE EXPRESSLY EXCLUDED.

