

# MOLYKOTE® G-1074 Grease

Polyalphaolefin (PAO) lubricating grease for multiple substrates; excellent noise-damping properties, even under extreme pressure at high frequency

## Features & benefits

- Excellent noise-damping performance/properties
- Fortified with additives to work under extreme pressure at high frequency
- Excellent wide temperature performance

## Composition

- Polyalphaolefin
- Lithium soap
- PTFE, antioxidants

## Applications

Automotive systems, such as chassis and brake, exterior, and interior. Ideal for bearings, gears, slides and mechanical applications requiring low friction and compatibility with common metals, plastics and/or elastomers.

## Description

MOLYKOTE® G-1074 Grease is a PAO-based grease for lubricating common metal, plastic and elastomeric substrates. It offers excellent noise-damping properties, even under extreme pressure at high frequency.

## How to use

Clean points of application. As is usual with lubricating greases, apply or fill by means of a brush, spatula or automated lubrication device.

## Handling precautions

PRODUCT SAFETY INFORMATION REQUIRED FOR SAFE USE IS NOT INCLUDED IN THIS DOCUMENT. BEFORE HANDLING, READ SAFETY DATA SHEETS AND CONTAINER LABELS FOR SAFE USE, PHYSICAL AND HEALTH HAZARD INFORMATION.

## Usable life and storage

When stored unopened in a cool, dark place, MOLYKOTE® G-1074 Grease has a usable life of 36 months from the date of production.

## Typical properties

Specification writers: These values are not intended for use in preparing specifications. Please contact your local MOLYKOTE® sales representative prior to writing specifications on this product.

| Standard <sup>(1)</sup> | Test   | Unit               | Result            |
|-------------------------|--|--------------------|-------------------|
|                         | Appearance   |                    | Translucent white |
| JIS K 2220              | Penetration  |                    | 280               |
|                         | Temperature range                                      | °C                 | -40 to 150        |
| JIS K 2283              | Base oil viscosity (40°C)                              | mm <sup>2</sup> /s | 53                |
|                         | Base oil viscosity (100°C)                             | mm <sup>2</sup> /s | 8.5               |
| JIS K 5600              | Density  | g/ml               | 0.90              |
| JIS K 2220              | Bleed (24 hrs, 100°C)                                  | %                  | 3.6               |
| JIS K 2220              | Evaporation loss (22 hrs, 99°C)                        | %                  | 0.1               |
| JIS K 2220              | Water washout test (38°C, 1 hr)                        | %                  | 1.98              |
| JIS K 2220              | Dropping point   | °C                 | 210               |
| ASTM D2266              | 4 ball test, wear scar (1,200 rpm, 392 N, 1 hr)        | mm                 | 0.69              |
| ASTM D5706              | SRV, extreme pressure (50°C, 50 Hz, 1 mm, Procedure A) | N                  | 1,000             |
| JIS K 2220              | Low-temperature torque (-40°C)                         |                    |                   |
|                         | Starting   | mNm                | 99                |
|                         | Running  | mNm                | 50                |

<sup>(1)</sup>JIS: Japanese Industrial Standard. ASTM: American Society for Testing and Materials.

## Packaging

This product is available in 1 kg cans (10 cans/case) and 16 kg pails.

*DuPont™, the DuPont Oval Logo, and all trademarks and service marks denoted with ™, SM or ® are owned by affiliates of DuPont de Nemours, Inc. unless otherwise noted.*  
© 2016-2019 DuPont.

The information set forth herein is furnished free of charge and is based on technical data that DuPont believes to be reliable and falls within the normal range of properties. It is intended for use by persons having technical skill, at their own discretion and risk. This data should not be used to establish specification limits nor used alone as the basis of design. Handling precaution information is given with the understanding that those using it will satisfy themselves that their particular conditions of use present no health or safety hazards. Since conditions of product use and disposal are outside our control, we make no warranties, express or implied, and assume no liability in connection with any use of this information. As with any product, evaluation under end use conditions prior to specification is essential. Nothing herein is to be taken as a license to operate or a recommendation to infringe on patents.