



# Krytox™ AUT 2E45

## Performance Lubricants

### Grease for Electric Motors

## Product Information

Krytox™ greases offer the potential for lubed-for-life properties in demanding electrical motor service. Krytox™ greases are non-oxidizing, water-resistant, nonflammable, and chemically inert.

Krytox™ greases contain perfluoropolyether (PFPE) oil and a polytetrafluoroethylene (PTFE) thickener. The PFPE oil and PTFE thickener will not oxidize and gum up like ordinary synthetic or hydrocarbon-based greases. Krytox™ greases are recommended by many major bearing manufacturers for long-life lubrication in severe applications. The superior film-forming capability of Krytox™ greases provide a thicker oil layer and reduce wear. Krytox™ greases are compatible with metals and most seal materials, but require removal of all old lubricants from the motor bearings before application.

### Benefits and Features

Krytox™ greases offer the following benefits and features.

| Feature                                      | Benefits                                                                                                                                                                                     |
|----------------------------------------------|----------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|
| Unsurpassed oxidation resistance of base oil | PFPE will not oxidize and gum up with age and use. Will not break down with high temperatures experienced in electric motors. Operating temperature range from -44 to 200 °C (-47 to 392 °F) |
| Advanced PTFE thickener                      | Special high efficiency thickener will not oxidize or break down with shear                                                                                                                  |
| Lubed-for-life potential                     | Typically, no need to re-lubricate bearings during lifetime of electric motor                                                                                                                |
| Excellent corrosion resistance               | Additives offer resistance to corrosion and rust during storage and in wet environments                                                                                                      |


### Typical Properties

| Property                                                                            | Krytox™ AUT 2E45 Grease    |
|-------------------------------------------------------------------------------------|----------------------------|
| NLGI Grade                                                                          | 2                          |
| Color                                                                               | White                      |
| Base Oil                                                                            | PFPE                       |
| Base Oil Viscosity, ASTM D 445<br>cSt at 40 °C (104 °F)<br>cSt at 100 °C (212 °F)   | 100<br>12.5                |
| Viscosity Index, ASTM D 2270                                                        | 119                        |
| Thickener                                                                           | PTFE                       |
| Anti-Corrosion Additive                                                             | Proprietary                |
| Specific Gravity at 0 °C (32 °F)                                                    | 2.0                        |
| Penetration Change after 100,000 strokes, ASTM D 217, mm/10                         | 15                         |
| Bearing Life, hr, ASTM D 3336, 10,000 rpm at 180 °C (356 °F)*                       | 25,000+                    |
| Operating Temperature Range, °C (°F)                                                | -44 to 200<br>(-47 to 392) |
| Dropping Point, °C (°F)                                                             | N/A                        |
| Oil Separation at 99 °C (210 °F), ASTM D 6184                                       | 4% typical                 |
| Low Temperature Torque, g·cm at -40 °C (-40 °F), ASTM D 1478<br>Starting<br>Running | 5,800<br>1,900             |
| Low Temperature Torque, g·cm at -20 °C (-4 °F), ASTM D 1478<br>Starting<br>Running  | 650<br>220                 |
| Emcor Corrosion, ASTM D 6138                                                        | 0, 1 (no rust)             |
| Rust Protection, ASTM D 1743                                                        | Pass                       |
| Copper Corrosion Resistance, ASTM D 4048                                            | 1B max.                    |
| Water Washout, ASTM D 1264, %                                                       | 1.5                        |


\* The ASTM D 3336 at 180 °C (356 °F) test for Krytox™ AUT 2E45 grease was still running when discontinued at 25,036 hr. Actual run time would have been longer.

Note: For application in wide profile bearings (e.g., cylindrical, spherical roller) at Dn > 70,000 (bearing mean diameter x rpm), please contact your Chemours technical representative for application assistance.

## ASTM D 3336—Grease Life in Ball Bearings—Krytox™ AUT 2E45 Lubricant



## Bench Bearing Life Test—ROF+—Krytox™ AUT 2E45 Lubricant



The information set forth herein is furnished free of charge and based on technical data that Chemours believes to be reliable. It is intended for use by persons having technical skill, at their own discretion and risk. The handling precaution information contained herein is given with the understanding that those using it will satisfy themselves that their particular conditions of use present no health or safety hazards. Because conditions of product use are outside our control, Chemours makes no warranties, express or implied, and assumes no liability in connection with any use of this information. As with any material, evaluation of any compound under end-use conditions prior to specification is essential. Nothing herein is to be taken as a license to operate under or a recommendation to infringe any patents.

NO PART OF THIS MATERIAL MAY BE REPRODUCED, STORED IN A RETRIEVAL SYSTEM OR TRANSMITTED IN ANY FORM OR BY ANY MEANS ELECTRONIC, MECHANICAL, PHOTOCOPYING, RECORDING OR OTHERWISE WITHOUT THE PRIOR WRITTEN PERMISSION OF CHEMOURS.

For product information, industry applications, technical assistance, or global distributor contacts, visit [krytox.com](http://krytox.com) or within the U.S. and Canada, call 1-844-773-CHEM/2436 or outside of the U.S., call 1-302-773-1000.

© 2015 The Chemours Company FC, LLC. Krytox™ and any associated logos are trademarks or copyrights of The Chemours Company FC, LLC. Chemours™ and the Chemours Logo are trademarks of The Chemours Company.

Replaces: K-23698-6

C-10071 (7/15)