

Advanced Materials**RenShape[®] BM 5166**

BOARD MATERIAL
SHEET METAL FORMING TOOLING BOARD

**KEY
PROPERTIES**

- Good abrasion resistance
- Low coefficient of thermal expansion
- Excellent compressive strength
- High density
- Good heat resistance
- Good machinability

APPLICATIONS

- Sheet metal forming tools
- Tooling jigs and fixtures

PRODUCT DATA

Product	Colour	Test method
RenShape BM 5166	Ivory	Visual

PROPERTIES

Density	ISO 1183	g/cm ³	1.7
Hardness	ISO 868	Shore D	85 - -90
Coefficient of thermal expansion	ISO 11359	10 ⁻⁶ K ⁻¹	45 - 50
Deflection temperature	ISO 75	°C	75 - 80
Compressive strength	ISO 604	MPa	90 - 100
Compressive modulus	ISO 604	MPa	7000 - 7500
Flexural strength	ISO 178	MPa	55 - 65

BONDING

System		Araldite[®] AW 106 HV 953U
Appearance	Visual	Transparent
Mix ratio	Parts by weight	100 : 60
Pot Life	min	60 - 90
Clamping time	h	12

Notes: Sheet metal forming

REPAIR

System		Araldite[®] AV 5308 HV 5309-1	RenPIM[®] 5219 A/B RenPIM[®] 5217 B DT 082
Appearance	visual	Beige thixotropic	Beige thixotropic
Mix ratio	Parts by weight	100 : 100	80 : 50 : 50 : 500
Pot life at 25°C	min	30 - 40	2 - 3
Cure time	h	15	2 - 3

Notes: Alternatively repair with adhesive bonded insert.
Araldite AW 106 and HV 953U are supplied in smaller packs than Araldite 2011.
Araldite AV 5308 and HV 5309 are supplied in smaller packs than Araldite 2015.

MILLING Milling parameter available on request.

STORAGE Board material may be stored flat in original cartons at 20o to 40o C in a dry area. Temperature variations should be avoided when transporting and storing board material.

WORKING CONDITION The product should be used when in the temperature range 20o to 25o C.

PACKAGING

Dimensions (mm)	Volume (l)	Weight (kg)	Number of Boards (per pack)	Number of Boards (per pallet)
750 x500X 50	16	26 - 30	2	24
750 x500x100	32	53 - 56	1	12

**HANDLING
PRECAUTIONS**

Caution
Our products are generally quite harmless to handle provided that certain precautions normally taken when handling chemicals are observed. The uncured materials must not, for instance, be allowed to come into contact with foodstuffs or food utensils, and measures should be taken to prevent the uncured materials from coming in contact with the skin, since people with particularly sensitive skin may be affected. The wearing of impervious rubber or plastic gloves will normally be necessary; likewise the use of eye protection. The skin should be thoroughly cleansed at the end of each working period by washing with soap and warm water. The use of solvents is to be avoided. Disposable paper - not cloth towels - should be used to dry the skin. Adequate ventilation of the working area is recommended. These precautions are described in greater detail in the Material Safety Data sheets for the individual products and should be referred to for fuller information.

Huntsman Advanced Materials
(Switzerland) GmbH
Klybeckstrasse 200
4057 Basel
Switzerland

Tel: +41 (0)61 299 11 11
Fax: +41 (0)61 299 11 12

www.huntsman.com/advanced_materials
Email: advanced_materials@huntsman.com



Huntsman Advanced Materials warrants only that its products meet the specifications agreed with the user. Specified data are analysed on a regular basis. Data which is described in this document as 'typical' or 'guideline' is not analysed on a regular basis and is given for information purposes only. Data values are not guaranteed or warranted unless if specifically mentioned.

The manufacture of materials is the subject of granted patents and patent applications; freedom to operate patented processes is not implied by this publication. While all the information and recommendations in this publication are, to the best of Huntsman Advanced Material's knowledge, information and belief, accurate at the date of publication, nothing herein is to be construed as a warranty, whether express or implied, including but without limitation, as to merchantability or fitness for a particular purpose. In all cases, it is the responsibility of the user to determine the applicability of such information and recommendations and the suitability of any product for its own particular purpose.

The behaviour of the products referred to in this publication in manufacturing processes and their suitability in any given end-use environment are dependent upon various conditions such as chemical compatibility, temperature, and other variables, which are not known to Huntsman Advanced Materials. It is the responsibility of the user to evaluate the manufacturing circumstances and the final product under actual end-use requirements and to adequately advise and warn purchasers and users thereof.

Products may be toxic and require special precautions in handling. The user should obtain Safety Data Sheets from Huntsman Advanced Materials containing detailed information on toxicity, together with proper shipping, handling and storage procedures, and should comply with all applicable safety and environmental standards.

Hazards, toxicity and behaviour of the products may differ when used with other materials and are dependent on manufacturing circumstances or other processes. Such hazards, toxicity and behaviour should be determined by the user and made known to handlers, processors and end users.

Except where explicitly agreed otherwise, the sale of products referred to in this publication is subject to the general terms and conditions of sale of Huntsman Advanced Materials LLC or of its affiliated companies including without limitation, Huntsman Advanced Materials (Europe) BVBA, Huntsman Advanced Materials Americas Inc., Huntsman Advanced Materials (UAE) FZE, Huntsman Advanced Materials (Guangdong) Company Limited, and Huntsman Advanced Materials (Hong Kong) Ltd.

Huntsman Advanced Materials is an international business unit of Huntsman Corporation. Huntsman Advanced Materials trades through Huntsman affiliated companies in different countries including but not limited to Huntsman Advanced Materials LLC in the USA and Huntsman Advanced Materials (Europe) BVBA in Europe.

All trademarks mentioned are either property of or licensed to Huntsman Corporation or an affiliate thereof in one or more, but not all, countries.

Copyright © 2012 Huntsman Corporation or an affiliate thereof. All rights reserved.