

## Dow Corning® 748 Non-Corrosive Sealant

### FEATURES

- ◆ One component adhesive/sealant
- ◆ Cures at room temperature when exposed to moisture in the air
- ◆ Alkoxy cure system
- ◆ Non sag, paste consistency
- ◆ Easy to apply
- ◆ Excellent adhesion to many substrates
- ◆ Stable and flexible form -55°C (-67°F) to +177°C (350°F)
- ◆ Complies with FDA 177.2600
- ◆ Meets UL 94 HB Flame Classification
- ◆ Complies with MIL-A- 46146

### BENEFITS

- ◆ Non Corrosive
- ◆ Low Odor

### COMPOSITION

- ◆ 100% Silicone Adhesive/Sealant

### Neutral cure silicone adhesive/sealant

### APPLICATIONS

- ◆ General industrial sealing and bonding applications where non-corrosive cure is required.
- ◆ Complies with MIL-A-46146, FDA 177.2600 and UL 94 HB

### TYPICAL PROPERTIES

Specifications writers: These values are not intended for use in preparing specifications. Please contact your local Dow Corning sales representative prior to writing specifications on this product.

Standard*	Property	Unit	Value
	Color		Off-white
<b>As supplied</b>			
CTM 0176	Consistency		Non-slump paste
CTM 0364	Extrusion Rate 3.2 mm orifice, 0.62 MPa	g/min	145
CTM 0098	Skin-Over-Time	min	15
CTM 0095	Tack-Free-Time	min	46
CTM 0097	Specific Gravity at 25°C		1.33
<b>As cured – 7 days at 25°C and 50% R.H.</b>			
ASTM D 2240	Hardness, Shore A		35
ASTM D 412	Tensile Strength	MPa	1.9
ASTM D 412	Elongation at Break	%	350
ASTM D 149	Dielectric Strength	kV/mm	18.7
ASTM D 257	Volume Resistivity	Ohm-cm	7.7 x 10 <sup>14</sup>
ASTM D 150	Dielectric Constant at 25°C		
	at 100 Hz		3.30
	at 10 kHz		3.21
ASTM D 150	Dissipation Factor at 25°C		
	at 100 Hz		8.7 x 10 <sup>-3</sup>
	at 10 kHz		2.8 x 10 <sup>-3</sup>
CTM 0293	Adhesion – Peel Strength Adhesion on Aluminum after 3 days at 25 °C	kN/m	7.0

\* CTM: Corporate Test Method

\* ASTM : American Society for Testing and Materials.

### DESCRIPTION

Dow Corning® 748 is a medium modulus silicone adhesive/sealant designed for applications where non-corrosive cure and durable adhesion is required.

isopropyl alcohol, acetone or methyl-ethyl ketone.

### HOW TO USE

#### Substrate preparation

All surfaces must be clean and dry. Degrease and wash off any contaminants that could impair adhesion. Suitable solvents include

Unprimed adhesion may be obtained by on many substrates such as glass, metals and most common engineering plastics. Adhesion may be less successful on some low energy plastics such as polyethylene, polypropylene and PTFE.

However, for maximum adhesion, the use of Dow Corning® 1200 OS Primer is recommended. After solvent cleaning, a thin coat of Dow Corning®

1200 OS Primer is applied by dipping, brushing or spraying. Allow primer to dry for 15 to 90 minutes at room temperature and a relative humidity of 50% or higher.

#### **How to apply**

*Dow Corning*<sup>®</sup> 748 is ready to use. Apply a bead of *Dow Corning*<sup>®</sup> 748 to one of the prepared surfaces, then quickly cover with the other substrate to be bonded. When placing the second surface, use enough pressure to displace the adhesive/sealant.

On exposure to moisture, the freshly applied material will “skin over” in about 15 minutes at room temperature and 50% relative humidity. Any tooling should be completed before this skin forms. The surface is easily tooled with a spatula. The adhesive/sealant will be tack-free in about 45 minutes.

The odor given off during cure is due to the release of an alcohol. The odor will disappear when the cure is complete.

#### **Cure Time**

After skin formation, cure continues inward from the surface. In 24 hours at room temperature and 50 % relative humidity, *Dow Corning*<sup>®</sup> 748 will cure to a depth of about 2 mm. Very deep sections, especially when access to atmospheric moisture is restricted, will take longer to cure completely. Cure time is extended at lower humidity levels.

Before handling and packaging bonded components, users are advised to wait a sufficiently long time to ensure that the integrity of the seal is not affected. This will depend on many factors and should be determined by the user for each specific application.

#### **HANDLING PRECAUTIONS**

Product safety information required for safe use is not included. Before handling, read product and safety data sheets and container labels for safe use, physical and health hazard information. The material safety data sheet is available on the Dow Corning website at [www.dowcorning.com](http://www.dowcorning.com). You can also obtain a copy from your local Dow Corning sales representative or Distributor or by calling your local Dow Corning Global Connection.

#### **USABLE LIFE AND STORAGE**

When stored at or below 32°C in the original unopened containers, this product has a usable life of 24 months from the date of production.

#### **PACKAGING**

This product is available in different standard container sizes. Detailed container size information should be obtained from your nearest Dow Corning Sales Office or Dow Corning Distributor.

#### **LIMITATIONS**

This product is neither tested nor represented as suitable for medical or pharmaceutical uses.

#### **SPECIFICATIONS**

##### **FDA Status**

When fully cured and washed, *Dow Corning*<sup>®</sup> 748 meets the requirements of FDA regulation No. 21 CFR 177.2600, subject to end-user compliance with any applicable total extractives limitations.

##### **UL Status**

*Dow Corning*<sup>®</sup> 748 is recognized by Underwriters Laboratories Inc. for service to 105 °C (356°F) where elongation is not essential. It also meets UL 94 Flame class, 94HB. UL File No. E 40195 (N)

##### **MIL-A-46146**

*Dow Corning*<sup>®</sup> 748 complies with the non corrosive requirements of MIL-A-46146 and can be supplied to this portion of the specification upon request.

#### **HEALTH AND ENVIRONMENTAL INFORMATION**

To support Customers in their product safety needs, Dow Corning has an extensive Product Stewardship organization and a team of Product Safety and Regulatory Compliance (PS&RC) specialists available in each area.

For further information, please see our website, [www.dowcorning.com](http://www.dowcorning.com) or consult your local Dow Corning representative.

#### **LIMITED WARRANTY INFORMATION - PLEASE READ CAREFULLY**

The information contained herein is offered in good faith and is believed to be accurate. However, because conditions and methods of use of our products are beyond our control, this information should not be used in substitution for customer's tests to ensure that Dow Corning's products are safe, effective, and fully satisfactory for the intended end use. Suggestions of use shall not be taken as inducements to infringe any patent.

Dow Corning's sole warranty is that the product will meet the Dow Corning sales specifications in effect at the time of shipment.

Your exclusive remedy for breach of such warranty is limited to refund of purchase price or replacement of any product shown to be other than as warranted.

**DOW CORNING SPECIFICALLY DISCLAIMS ANY OTHER EXPRESS OR IMPLIED WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE OR MERCHANTABILITY.**

**DOW CORNING DISCLAIMS LIABILITY FOR ANY INCIDENTAL OR CONSEQUENTIAL DAMAGES.**

*We help you invent the future.™*

[www.dowcorning.com](http://www.dowcorning.com)