Data Sheet

18, ZI Haneboesch L-4562 Differdange LUXEMBOURG Phone: +352 58 22 82 1 Fax: +352 58 49 35 E-mail : sales@airtech.lu Website : www.airtech.lu

WRIGHTLON® 8400

Nylon vacuum bagging film

DESCRIPTION

Wrightlon® 8400 is a high temperature nylon vacuum bagging film with more than 30 years worldwide proven performance. It is called out on many aerospace specifications for use temperatures up to 232°C. It is recommended for cures with phenolic resins.

BENEFITS

- Heat resistance provides vacuum security during high temperature cures of expensive parts.
- Proven performance and approvals on specifications worldwide gained over more than 30 years.
- High strength and chemical resistance reduces bag failures with aggressive phenolic resins.

TECHNICAL DATA

		Test method
Material type	Nylon	
Elongation at break	350 %	ASTM D 882
Tensile strength	62 MPa	ASTM D 882
Maximum use temperature	232°C	

Flammability (self extinguishing) Yes ATP-5034

Materials to avoid Strong oxidizers

Colour Blue

Shelf life Unlimited when stored in original packaging at 22°C

SIZES

Thickness	Width	Forms Available*
50 μm (0,002 inch)	up to 3,66 m (144 inches)	SHT, CF, LFT
75 μm (0,003 inch)	up to 4,57 m (180 inches)	SHT, CF, LFT

- For more sizes, see the Commonly Used Sizes chart in this section.
- Custom shapes and sizes are available, please contact Airtech for more information.







CF=Centerfold



LFT=Lay-Flat Tubing



GT=Gusseted Tubing



NOTES

• The maximum use temperature is dependent upon the duration at maximum temperature and is process specific, Airtech recommends testing prior to use.

Last updated: 2020-06-16
Catalogue position: Bagging films