

Advanced Materials**Epocast[®] 1652-A/B****EPOXY SYNTACTIC**

- Low Density Syntactic
- Thick Paste Consistency
- High Compressive Strength

DESCRIPTION :

Epocast[®] 1652-A/B epoxy syntactic is a low-density system with good elevated temperature performance after a room-temperature cure. The epoxy syntactic is suitable for core filling metal skins, adding stiffness and strength to fabricated parts such as helicopter rotor blades, core splicing, and strengthening radii and corners of reinforced plastic structures. Epocast[®] 1652-A/B epoxy syntactic is qualified to Grumman GM 4006, Gulfstream GMS 4005 and Sikorsky 9587, Type 2.

TYPICAL PROPERTIES AS RECEIVED :

<u>Property</u>	<u>1652-A Resin</u>	<u>1652-B Hardener</u>	<u>1652-A/B System</u>	<u>Test Method</u>
Color	Light Tan	Amber	Light Tan	Visual
Density, g/cc.	0.80	1.00	0.8	ASTM-1622
Viscosity, cP at 77°F (25°C)	Paste	500	Semi-paste	ASTM-D-2196
Gel time, 100 gms at 77°F (25°C), minutes	--	--	30-60	ASTM-D-2471

MIX RATIO :

To 100 parts by weight of Epocast[®] 1652-A resin, add 12 parts by weight of Epocast[®] 1652-B hardener. Mix both components thoroughly for several minutes to insure complete blending.

CURE SCHEDULE :

Seven days at 77°F (25°C), or gel at 77°F (25°C) followed by 2-3 hours at 150°F (66°C).

TYPICAL CURED PROPERTIES (Not for specification purposes)

Test	Result	Test Method
Compressive strength, Ksi (MPa) (2% strain) @ -67°F (-55°C)	9.50 (65.5)	ASTM-D-695
@ 77°F (25°C)	8.00 (55)	--
@ 180°F (83°C)	4.00 (27.6)	--
@ 350°F (177°C)	0.65 (4.5)	--
Ultimate compressive strength, Ksi (MPa) @ 77°F (25°C)	9.00 (62)	--
Tensile lap shear, (etched AL/AL), @ 77°F (25°C), psi (MPa)	700 (4.8)	ASTM-D-1002

STORAGE:

Epocast[®] 1652-A/B should be stored in a dry place, in the sealed original container, at temperatures between +2°C and +40°C (+35.6°F and 104°F). The product should not be exposed to direct sunlight. Under these storage conditions, and when supplied under Huntsman standard certification, this product has a shelf life of 1 year (expiration date may differ based on customer specification).

Material temperatures should be above 18°C (65°F) when mixing. After use, tightly reseal containers.

PRECAUTIONARY STATEMENT

Huntsman Advanced Materials Americas LLC maintains up-to-date Material Safety Data Sheets (MSDS) on all of its products. These sheets contain pertinent information that you may need to protect your employees and customers against any known health or safety hazards associated with our products. Users should review the latest MSDS to determine possible health hazards and appropriate precautions to implement prior to using this material.

First Aid!

Refer to MSDS as mentioned above.

KEEP OUT OF REACH OF CHILDREN**FOR PROFESSIONAL AND INDUSTRIAL USE ONLY**

IMPORTANT LEGAL NOTICE

Sales of the product described herein ("Product") are subject to the general terms and conditions of sale of either Huntsman Advanced Materials LLC, or its appropriate affiliate including without limitation Huntsman Advanced Materials (Europe) BVBA, Huntsman Advanced Materials Americas Inc., or Huntsman Advanced Materials (Hong Kong) Ltd. ("Huntsman"). The following supercedes Buyer's documents.

Huntsman warrants that at the time and place of delivery all Products sold to Buyer shall conform to the specifications provided to Buyer by Huntsman.

While the information and recommendations included in this publication are, to the best of Huntsman's knowledge, accurate as of the date of publication, NOTHING CONTAINED HEREIN (EXCEPT AS SET FORTH ABOVE REGARDING CONFORMANCE WITH SPECIFICATIONS PROVIDED TO BUYER BY HUNTSMAN) IS TO BE CONSTRUED AS A REPRESENTATION OR WARRANTY OF ANY KIND, EXPRESS OR IMPLIED, INCLUDING BUT NOT LIMITED TO ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, NONINFRINGEMENT OF ANY INTELLECTUAL PROPERTY RIGHTS, OR WARRANTIES AS TO QUALITY OR CORRESPONDENCE WITH PRIOR DESCRIPTION OR SAMPLE, AND THE BUYER ASSUMES ALL RISK AND LIABILITY WHATSOEVER RESULTING FROM THE USE OF SUCH PRODUCT, WHETHER USED SINGLY OR IN COMBINATION WITH OTHER SUBSTANCES.

No statements or recommendations made herein are to be construed as a representation about the suitability of any Product for the particular application of Buyer or user or as an inducement to infringe any patent or other intellectual property right. Buyer is responsible to determine the applicability of such information and recommendations and the suitability of any Product for its own particular purpose, and to ensure that its intended use of the Product does not infringe any intellectual property rights.

The Product may be or become hazardous. The Buyer should obtain Material Safety Data Sheets and Technical Data Sheets from Huntsman containing detailed information on Product hazards and toxicity, together with proper shipping, handling and storage procedures for the Product, and should comply with all applicable governmental laws, regulations and standards relating to the handling, use, storage, distribution and disposal of, and exposure to the Product. Buyer shall also take all steps necessary to adequately inform, warn and familiarize its employees, agents, direct and indirect customers and contractors who may handle or be exposed to the Product of all hazards pertaining to and proper procedures for safe handling, use, storage, transportation and disposal of and exposure to the Product, and the containers or equipment in which the Product may be handled, shipped or stored.

Epocast is a registered trademark of Huntsman LLC or an affiliate thereof in one or more countries, but not all countries.

© 2006 Huntsman Advanced Materials Americas Inc.

Main Offices :
Huntsman Corporation
10003 Woodloch Forest Dr.
The Woodlands
Texas 77380
(281) 719-6000

**Huntsman Advanced Technology
Center**
8600 Gosling Rd.
The Woodlands
Texas 77381
(281) 719-7400