

## Epibond® 215 A/B High Strength Adhesive

### Product Description

Epibond® 215 A/B Adhesive is an extrudable, two-component, room temperature-curing epoxy structural adhesive designed for service temperatures up to 300°F (149°C). This adhesive is suitable for bonding a wide variety of materials such as metals, composites and many other dissimilar substrates. The combination of high peel strength and high shear makes this adhesive well suited for aerospace and other demanding applications.

### Features

- Room Temperature cure
- Fast Handling Strength
- Outstanding Peel and High Shear Strength
- Service Temperature from -90°F (-68°C) to 300°F (149°C)
- Good retention of strength after environmental aging or chemical immersion
- Gap-filling thixotropic paste
- 2:1 mix ratio by weight and volume
- Low Outgassing
- No SVHC as defined under REACH (*Does not intentionally contain any Substances of Very High Concern (SVHC) as published by the European Chemicals Agency (ECHA) pursuant to Article 59 REACH as of October 11, 2016*)

### Processing

Under normal temperature conditions and when used with the recommended mix ratio this adhesive will typically provide a working time of approximately 60 - 70 minutes (20 g). Substrates to be bonded should be properly surface treated and be free from any contaminants. Mix both components thoroughly for several minutes until a homogeneous mixture is obtained, or dispense from a 2:1 200ml dual barrel cartridge. For the 200 mL size, use TAH 10-mm dia. x 24-element spiral mixing nozzle or equivalent.

### Application

The mixed adhesive should be spread with a spatula to the suitably pretreated dry joint surfaces. A layer of adhesive 0.004 to 0.012 inches (0.1 to 0.3 mm) thick will normally provide the maximum lap shear strength. This adhesive, however, has been designed to be effective in layers up to 0.12 in. (3 mm). The components to be bonded should be assembled and clamped as soon as the adhesive has been applied. Even contact pressure throughout the joint area during cure will ensure optimum performance.

### Typical Properties\*

| Property                              | Epibond® 215 A | Epibond® 215 B | Mixed System  |
|---------------------------------------|----------------|----------------|---------------|
| Appearance                            | Off-white      | Amber          | Off-white     |
| Density g/cm <sup>3</sup> [ASTM D792] | 1.1            | 1.1            | 1.1           |
| Viscosity, cP [ASTM D2196]            | Paste          | Paste          | Non-sag Paste |

\*Typical properties are based on Huntsman's test methods. Copies are available upon request.

### Mixing

| Product                 | Parts by weight | Parts by volume |
|-------------------------|-----------------|-----------------|
| Epibond® 215 A Resin    | 100             | 2               |
| Epibond® 215 B Hardener | 45              | 1               |

### Processing Data

| Parameter                      | Value                                     |
|--------------------------------|-------------------------------------------|
| Pot Life, in nozzle            | 30 min                                    |
| Gel Time, 20 g, at 77°F (25°C) | 100 min                                   |
| Typical Cure Cycles            | 1 hour at 150°F, or<br>4 - 5 days at 77°F |

### Handling Strength

Measured by lap shear strength with PPA and primed Aluminum at RT, in psi (MPa)

| Cure time, hours | Cure Temperature |              |
|------------------|------------------|--------------|
|                  | 77°F (25°C)      | 150°F (66°C) |
| 1                | NA               | 5,100 (35.1) |
| 3                | 570 (3.9)        | NA           |
| 4                | 2,390 (16.5)     | NA           |
| 5                | 3,150 (21.7)     | NA           |
| 24               | 4,600 (31.7)     | NA           |

\*NA = not tested

### Typical Physical Properties

Unless otherwise stated, the data were determined with typical production batches using standard test methods. They are typical values only, and do not constitute a product specification.

# Advanced Materials

## Technical Datasheet

Tests were done on prepared samples, such as phosphoric acid anodized and primed aluminum with appropriate surface treatment. Surfaces of steels and plastics were prepared by abrading with 210 grit sand paper / IPA wiping / Lint free towel drying / Nitrogen blowing. Unless otherwise noted, samples were cured 5 days at 77°F, and tested at 77°F (25°C).

| Property                                                        |                                                    | Value                  |
|-----------------------------------------------------------------|----------------------------------------------------|------------------------|
| Lap shear strength, psi (MPa)                                   |                                                    |                        |
| Anodized & Primed Aluminum [ASTM D1002]                         |                                                    |                        |
| Cured 24 hours at 77°F (25°C)                                   |                                                    |                        |
| -67°F (-55°C)                                                   |                                                    | 5,400 (37.2)           |
| 73°F (23°C)                                                     |                                                    | 4,600 (31.7)           |
| 180°F (82°C)                                                    |                                                    | 3,500 (24.1)           |
| 250°F (121°C)                                                   |                                                    | 1,250 (8.6)            |
| Cured 5 days at 77°F (25°C)                                     |                                                    |                        |
| -90°F (-68°C)                                                   |                                                    | 5,500 (37.9)           |
| 73°F (23°C)                                                     |                                                    | 5,200 (35.8)           |
| 250°F (121°C)                                                   |                                                    | 2,000 (13.8)           |
| 300°F (149°C)                                                   |                                                    | 1,100 (7.6)            |
| Cured 77°F/3hr + 250°F/1hr                                      |                                                    |                        |
| 73°F (23°C)                                                     |                                                    | 5,400 (37.2)           |
| Composites & Plastics [ASTM D5868]                              |                                                    |                        |
| CFRP-CFRP                                                       |                                                    | 3,000 (20.7)           |
| ABS-ABS                                                         |                                                    | 660 (4.5)              |
| PVC-PVC                                                         |                                                    | 490 (3.4)              |
| PC-PC                                                           |                                                    | 540 (3.7)              |
| PEI-PEI                                                         |                                                    | 970 (6.7)              |
| Nylon-Nylon                                                     |                                                    | 650 (4.5)              |
| After Environmental and Chemical Exposure, 30 days [ASTM D1002] |                                                    |                        |
| 120°F (49°C), 95% RH                                            |                                                    | 4,600 (31.7)           |
| Jet Fluid at 73°F (23°C)                                        |                                                    | 5,100 (35.1)           |
| 50/ 50 Antifreeze at 180°F (82°C)                               |                                                    | 4,390 (30.2)           |
| MEK at 73°F (23°C)                                              |                                                    | 5,280 (36.4)           |
| Skydrol at 150°F (66°C)                                         |                                                    | 5,345 (36.8)           |
| Roller peel strength, pli (N/mm) [ASTM D3167]                   |                                                    | 85 (14.9)              |
| Anodized & Primed Aluminum                                      |                                                    |                        |
| T- peel strength, pli (N/mm) [ASTM D1876]                       |                                                    | 71 (12.4)              |
| Anodized & Primed Aluminum                                      |                                                    |                        |
| Compressive strength, psi (MPa) [ASTM D695]                     |                                                    | 7,400 (75.8)           |
| Compressive modulus, ksi (MPa) [ASTM D695]                      |                                                    | 360 (2,475)            |
| Hardness, Shore D [ASTM D2250]                                  |                                                    | 80                     |
| Tg, DMA, °C (°F) [ASTM E1640]                                   | Storage Modulus Onset, °C<br>Loss Modulus Peak, °C | 64<br>71               |
| CTE, mm/mm/°C [ASTM E831]                                       | Below Tg                                           | 1.019x10 <sup>-4</sup> |
|                                                                 | Above Tg                                           | 1.872x10 <sup>-4</sup> |
| Outgassing [ASTM E595]                                          | TML, %                                             | 0.91                   |
|                                                                 | CVCM, %                                            | < 0.01                 |
|                                                                 | WVR, %                                             | 0.41                   |

## Storage

**Epibond® 215 A/B Epoxy Adhesives** should be stored in a dry place in the original sealed container at temperatures between **2°C and 40°C (36°F and 104°F)**. Tightly reseal containers after each use. Under these storage conditions, the products have a shelf-life of **365 days from date of manufacture**. The components should not be exposed to direct sunlight.

## Precautionary Statement

Huntsman Advanced Materials Americas LLC maintains up-to-date Safety Data Sheets (SDS) on all of its products. These sheets contain pertinent information that you may need to protect your employees and customers against any known health or safety hazards associated with our products. Users should review the latest MSDS to determine possible health hazards and appropriate precautions to implement prior to using this material.

### First Aid!

Refer to SDS as mentioned above.

**KEEP OUT OF REACH OF CHILDREN**

**FOR PROFESSIONAL AND INDUSTRIAL USE ONLY**

### Important Legal Notice

Sales of the product described herein ("Product") are subject to the general terms and conditions of sale of either Huntsman Advanced Materials LLC, or its appropriate affiliate including without limitation Huntsman Advanced Materials (Europe) BVBA, Huntsman Advanced Materials Americas Inc., or Huntsman Advanced Materials (Hong Kong) Ltd. ("Huntsman"). The following supersedes Buyer's documents.

Huntsman warrants that at the time and place of delivery all Products sold to Buyer shall conform to the specifications provided to Buyer by Huntsman.

While the information and recommendations included in this publication are, to the best of Huntsman's knowledge, accurate as of the date of publication, NOTHING CONTAINED HEREIN (EXCEPT AS SET FORTH ABOVE REGARDING CONFORMANCE WITH SPECIFICATIONS PROVIDED TO BUYER BY HUNTSMAN) IS TO BE CONSTRUED AS A REPRESENTATION OR WARRANTY OF ANY KIND, EXPRESS OR IMPLIED, INCLUDING BUT NOT LIMITED TO ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, NONINFRINGEMENT OF ANY INTELLECTUAL PROPERTY RIGHTS, OR WARRANTIES AS TO QUALITY OR CORRESPONDENCE WITH PRIOR DESCRIPTION OR SAMPLE, AND THE BUYER ASSUMES ALL RISK AND LIABILITY WHATSOEVER RESULTING FROM THE USE OF SUCH PRODUCT, WHETHER USED SINGLY OR IN COMBINATION WITH OTHER SUBSTANCES.

No statements or recommendations made herein are to be construed as a representation about the suitability of any Product for the particular application of Buyer or user or as an inducement to infringe any patent or other intellectual property right. Buyer is responsible to determine the applicability of such information and recommendations and the suitability of any Product for its own particular purpose, and to ensure that its intended use of the Product does not infringe any intellectual property rights.

The Product may be or become hazardous. The Buyer should obtain Material Safety Data Sheets and Technical Data Sheets from Huntsman containing detailed information on Product hazards and toxicity, together with proper shipping, handling and storage procedures for the Product, and should comply with all applicable governmental laws, regulations and standards relating to the handling, use, storage, distribution and disposal of, and exposure to the Product. Buyer shall also take all steps necessary to adequately inform, warn and familiarize its employees, agents, direct and indirect customers and contractors who may handle or be exposed to the Product of all hazards pertaining to and proper procedures for safe handling, use, storage, transportation and disposal of and exposure to the Product, and the containers or equipment in which the Product may be handled, shipped or stored.

**Epibond** is a registered trademark of Huntsman LLC or an affiliate thereof in one or more, but not all countries.

© 2019 Huntsman Advanced Materials Inc.

#### Main Offices:

**Huntsman Corporation**  
10003 Woodloch Forest Dr  
The Woodlands, TX 77380  
888-564-9318

**Huntsman Advanced Technology Center**  
8600 Gosling Rd.  
The Woodlands, TX 77381  
281-829-7400