

## Advanced Materials

# Araldite® LY 5052 / Aradur® 5052\*

## COLD CURING EPOXY SYSTEMS

Araldite® LY 5052 is a low viscosity epoxy resin  
Aradur® 5052 is a mixture of polyamines

|                                  |                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                         |         |  |                 |              |  |                                  |                |         |                             |      |         |                          |                |         |                 |              |  |                                  |            |         |                             |      |         |                        |                |         |
|----------------------------------|-------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|---------|--|-----------------|--------------|--|----------------------------------|----------------|---------|-----------------------------|------|---------|--------------------------|----------------|---------|-----------------|--------------|--|----------------------------------|------------|---------|-----------------------------|------|---------|------------------------|----------------|---------|
| APPLICATIONS                     | Aerospace and industrial composites, tooling, aircraft repair.                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                          |         |  |                 |              |  |                                  |                |         |                             |      |         |                          |                |         |                 |              |  |                                  |            |         |                             |      |         |                        |                |         |
| PROPERTIES                       | <ul style="list-style-type: none"><li>• Low viscosity, easy impregnation of reinforcement materials.</li><li>• Long potlife (2 hours for 100 ml at ambient), ample processing time allows production of big objects.</li><li>• High temperature resistance (glass transition temperature) after ambient cure: 60 °C, after post-cure at 100:120 °C.</li><li>• Excellent mechanical and dynamic properties after ambient cure with potential for even higher properties after post-cure at elevated temperatures.</li><li>• Also laminates show outstanding mechanical and dynamic properties. This system is qualified by the Luftfahrtbundesamt (German Aircraft Authority) for the production of gliders.</li></ul> <p>Adequate skin protection is indispensable.</p> |         |  |                 |              |  |                                  |                |         |                             |      |         |                          |                |         |                 |              |  |                                  |            |         |                             |      |         |                        |                |         |
| PROCESSING                       | <ul style="list-style-type: none"><li>• Wet lay-up</li><li>• Resin Transfer Moulding (RTM)</li><li>• Pressure Moulding</li><li>• Filament Winding</li></ul>                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                             |         |  |                 |              |  |                                  |                |         |                             |      |         |                          |                |         |                 |              |  |                                  |            |         |                             |      |         |                        |                |         |
| PRODUCT DATA                     | <b>Araldite® LY 5052</b> <table><tr><td>Aspect (visual)</td><td>clear liquid</td><td></td></tr><tr><td>Viscosity at 25 °C (ISO 12058-1)</td><td>1000 – 1500 **</td><td>[mPa s]</td></tr><tr><td>Density at 25 °C (ISO 1675)</td><td>1.17</td><td>[g/cm³]</td></tr><tr><td>Epoxide index (ISO 3001)</td><td>6.65 – 6.85 **</td><td>[Eq/kg]</td></tr></table> <b>Aradur® 5052</b> <table><tr><td>Aspect (visual)</td><td>clear liquid</td><td></td></tr><tr><td>Viscosity at 25 °C (ISO 12058-1)</td><td>40 – 60 **</td><td>[mPa s]</td></tr><tr><td>Density at 25 °C (ISO 1675)</td><td>0.94</td><td>[g/cm³]</td></tr><tr><td>Amine value (ISO 9702)</td><td>9.55 – 9.75 **</td><td>[Eq/kg]</td></tr></table>                                                            |         |  | Aspect (visual) | clear liquid |  | Viscosity at 25 °C (ISO 12058-1) | 1000 – 1500 ** | [mPa s] | Density at 25 °C (ISO 1675) | 1.17 | [g/cm³] | Epoxide index (ISO 3001) | 6.65 – 6.85 ** | [Eq/kg] | Aspect (visual) | clear liquid |  | Viscosity at 25 °C (ISO 12058-1) | 40 – 60 ** | [mPa s] | Density at 25 °C (ISO 1675) | 0.94 | [g/cm³] | Amine value (ISO 9702) | 9.55 – 9.75 ** | [Eq/kg] |
| Aspect (visual)                  | clear liquid                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                            |         |  |                 |              |  |                                  |                |         |                             |      |         |                          |                |         |                 |              |  |                                  |            |         |                             |      |         |                        |                |         |
| Viscosity at 25 °C (ISO 12058-1) | 1000 – 1500 **                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                          | [mPa s] |  |                 |              |  |                                  |                |         |                             |      |         |                          |                |         |                 |              |  |                                  |            |         |                             |      |         |                        |                |         |
| Density at 25 °C (ISO 1675)      | 1.17                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                    | [g/cm³] |  |                 |              |  |                                  |                |         |                             |      |         |                          |                |         |                 |              |  |                                  |            |         |                             |      |         |                        |                |         |
| Epoxide index (ISO 3001)         | 6.65 – 6.85 **                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                          | [Eq/kg] |  |                 |              |  |                                  |                |         |                             |      |         |                          |                |         |                 |              |  |                                  |            |         |                             |      |         |                        |                |         |
| Aspect (visual)                  | clear liquid                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                            |         |  |                 |              |  |                                  |                |         |                             |      |         |                          |                |         |                 |              |  |                                  |            |         |                             |      |         |                        |                |         |
| Viscosity at 25 °C (ISO 12058-1) | 40 – 60 **                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                              | [mPa s] |  |                 |              |  |                                  |                |         |                             |      |         |                          |                |         |                 |              |  |                                  |            |         |                             |      |         |                        |                |         |
| Density at 25 °C (ISO 1675)      | 0.94                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                    | [g/cm³] |  |                 |              |  |                                  |                |         |                             |      |         |                          |                |         |                 |              |  |                                  |            |         |                             |      |         |                        |                |         |
| Amine value (ISO 9702)           | 9.55 – 9.75 **                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                          | [Eq/kg] |  |                 |              |  |                                  |                |         |                             |      |         |                          |                |         |                 |              |  |                                  |            |         |                             |      |         |                        |                |         |

\*\* Specified data are on a regular basis analysed. Data which is described in this document as 'typical' is not analysed on a regular basis and is given for information purposes only. Data values are not guaranteed or warranted unless if specifically mentioned.

|                |                                                                                                                                                                                                                                                                                                        |
|----------------|--------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|
| <b>STORAGE</b> | <p>Provided that the products described above are stored in a dry place in their original, properly closed containers at the above mentioned storage temperatures they will have the shelf lives indicated on the labels.</p> <p>Partly emptied containers should be closed immediately after use.</p> |
|----------------|--------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|

\* In addition to the brand name product denomination may show different appendices, which allows us to differentiate between our production sites: e.g., BD = Germany, US = United States, IN = India, CI = China, etc.. These appendices are in use on packaging, transport and invoicing documents. Generally the same specifications apply for all versions. Please address any additional need for clarification to the appropriate Huntsman contact.

## TYPICAL SYSTEM DATA

### PROCESSING DATA

| MIX RATIO | Components        | Parts by weight | Parts by volume |
|-----------|-------------------|-----------------|-----------------|
|           | Araldite® LY 5052 | 100             | 100             |
|           | Aradur® 5052      | 38              | 47              |

The components must be weighed accurately and mixed thoroughly to obtain optimal properties. The sides and bottom of mixing vessels must be included in the mixing process. Large mix quantities will show considerable exotherm, leading to short potlives. Preferably mix smaller quantities or divide large mixes into smaller containers.

| INITIAL MIX VISCOSITY<br>(ISO 12058-1) | [°C]  | [mPa s]     |
|----------------------------------------|-------|-------------|
|                                        | at 18 | 1150 - 1350 |
|                                        | at 25 | 500 - 700   |
|                                        | at 40 | 200 - 250   |

| VISCOSITY BUILD-UP<br>(ISO 12058-1) | [°C]  | [mPa s] | [min]    |
|-------------------------------------|-------|---------|----------|
|                                     | at 25 | to 1500 | 50 - 60  |
|                                     | at 25 | to 3000 | 90 - 110 |
|                                     | at 40 | to 1500 | 40 - 45  |
|                                     | at 40 | to 3000 | 50 - 60  |
|                                     | at 60 | to 1500 | 15 - 18  |
|                                     | at 60 | to 3000 | 18 - 22  |

| POT LIFE<br>(TECAM, 100 ML,<br>65 % RH) | [°C]  | [min]     |
|-----------------------------------------|-------|-----------|
|                                         | at 18 | 280 - 320 |
|                                         | at 25 | 110 - 160 |
|                                         | at 40 | 45 - 55   |

| GEL TIME<br>(HOT PLATE) | [°C]   | [min]     |
|-------------------------|--------|-----------|
|                         | at 25  | 420 - 500 |
|                         | at 40  | 150 - 170 |
|                         | at 60  | 40 - 55   |
|                         | at 80  | 14 - 17   |
|                         | at 100 | 4 - 6     |
|                         | at 120 | 2 - 3     |

The values shown are for small amounts of pure resin/hardener mix. In practice, fibre content and laminate thickness may modify the gel time to a very significant extent. In composite structures the gel time can differ significantly from the given values depending on the fibre content and the laminate thickness.

| GELATION AT 23 °C<br>(IN THIN LAYERS:<br>0.4 - 0.7 MM) |       | [h]     |
|--------------------------------------------------------|-------|---------|
|                                                        | Start | 5 - 6.5 |
|                                                        | End   | 7 - 8   |

| TYPICAL CURE CYCLES | 1 day 23 °C + 15 h 50 °C<br>or 1 day 23 °C + 4 h 100 °C |
|---------------------|---------------------------------------------------------|
|---------------------|---------------------------------------------------------|

The optimum cure cycle has to be determined case by case, depending on the processing and the economic requirements.

## PROPERTIES OF THE CURED, NEAT FORMULATION

| GLASS TRANSITION TEMPERATURE                             |                                                                                                                                                                   | Cure:                       | $T_G$ onset [°C] |             | $T_G$ [°C]  |
|----------------------------------------------------------|-------------------------------------------------------------------------------------------------------------------------------------------------------------------|-----------------------------|------------------|-------------|-------------|
| (ISO 11357-2,<br>DSC, 10 K/MIN)                          |                                                                                                                                                                   | 2 days 25 °C                |                  | 50 - 52     | 52 - 55     |
|                                                          |                                                                                                                                                                   | 8 days 25 °C                |                  | 60 - 64     | 62 - 66     |
|                                                          |                                                                                                                                                                   | 4 month 23 °C               |                  | 64 - 68     | 67 - 71     |
|                                                          |                                                                                                                                                                   | 1 day 23 °C + 10 h 40 °C    |                  | 68 - 72     | 70 - 76     |
|                                                          |                                                                                                                                                                   | 1 day 23 °C + 20 h 40 °C    |                  | 72 - 76     | 74 - 80     |
|                                                          |                                                                                                                                                                   | 1 day 23 °C + 10 h 50 °C    |                  | 78 - 82     | 80 - 85     |
|                                                          |                                                                                                                                                                   | 1 day 23 °C + 15 h 50 °C    |                  | 81 - 85     | 82 - 88     |
|                                                          |                                                                                                                                                                   | 1 day 23 °C + 10 h 60 °C    |                  | 92 - 96     | 94 - 104    |
|                                                          |                                                                                                                                                                   | 1 day 23 °C + 15 h 60 °C    |                  | 94 - 98     | 96 - 106    |
|                                                          |                                                                                                                                                                   | 1 day 23 °C + 2 h 80 °C     |                  | 106 - 110   | 108 - 114   |
|                                                          |                                                                                                                                                                   | 1 day 23 °C + 8 h 80 °C     |                  | 112 - 116   | 114 - 122   |
|                                                          |                                                                                                                                                                   | 1 day 23 °C + 1 h 90 °C     |                  | 104 - 108   | 108 - 118   |
|                                                          |                                                                                                                                                                   | 1 day 23 °C + 4 h 90 °C     |                  | 112 - 116   | 116 - 126   |
|                                                          |                                                                                                                                                                   | 1 day 23 °C + 1 h 100 °C    |                  | 116 - 120   | 118 - 130   |
|                                                          |                                                                                                                                                                   | 1 day 23 °C + 4 h 100 °C    |                  | 118 - 124   | 120 - 134   |
|                                                          | Even if post-cured at elevated temperature <u>after</u> a prolonged cure at ambient, a good increase of the glass transition temperature is obtained as follows : |                             |                  |             |             |
|                                                          |                                                                                                                                                                   | 4 months 23 °C + 4 h 130 °C |                  | 106 - 112   | 120 - 132   |
|                                                          |                                                                                                                                                                   |                             |                  |             |             |
| TENSILE TEST<br>(ISO 527)                                |                                                                                                                                                                   | Cure:                       | 7 days RT        | 15 h 50 °C  | 8 h 80 °C   |
|                                                          | Tensile strength                                                                                                                                                  | [MPa]                       | 49 - 71          | 82 - 86     | 84 - 86     |
|                                                          | Elongation at tensile strength                                                                                                                                    | [%]                         | 1.5 - 2.5        | 3.1 - 3.7   | 5.7 - 5.9   |
|                                                          | Ultimate strength                                                                                                                                                 | [MPa]                       | 49 - 71          | 80 - 83     | 80 - 84     |
|                                                          | Ultimate elongation                                                                                                                                               | [%]                         | 1.5 - 2.5        | 3.5 - 5.5   | 7.0 - 8.5   |
|                                                          | Tensile modulus                                                                                                                                                   | [MPa]                       | 3350 - 3550      | 3450 - 3650 | 3000 - 3200 |
|                                                          |                                                                                                                                                                   |                             |                  |             |             |
| FLEXURAL TEST<br>(ISO 178)                               |                                                                                                                                                                   | Cure:                       | 15 h 50 °C       |             | 8 h 80 °C   |
|                                                          | Flexural strength                                                                                                                                                 | [MPa]                       | 130 - 140        |             | 116 - 122   |
|                                                          | Elongation at flexural strength                                                                                                                                   | [%]                         | 5.8 - 6.3        |             | 6.5 - 7.2   |
|                                                          | Ultimate strength                                                                                                                                                 | [MPa]                       | 90 - 115         |             | 87 - 113    |
|                                                          | Ultimate elongation                                                                                                                                               | [%]                         | 8.0 - 9.5        |             | 8.5 - 13.4  |
|                                                          | Flexural modulus                                                                                                                                                  | [MPa]                       | 3000 - 3300      |             | 2700 - 3000 |
|                                                          |                                                                                                                                                                   |                             |                  |             |             |
| FRACTURE PROPERTIES<br>BEND NOTCH TEST<br>(ISO 13586)    |                                                                                                                                                                   | Cure:                       |                  |             | 8 h 80 °C   |
|                                                          | Fracture toughness $K_{1C}$                                                                                                                                       | MPa√m                       |                  |             | 0.77-0.83   |
|                                                          | Fracture energy $G_{1C}$                                                                                                                                          | [J/m <sup>2</sup> ]         |                  |             | 192 - 212   |
|                                                          |                                                                                                                                                                   |                             |                  |             |             |
| WATER ABSORPTION<br>(ISO 62)                             |                                                                                                                                                                   | Immersion:                  | Cure:            | 7 days RT   | 8 h 80 °C   |
|                                                          | 4 days H <sub>2</sub> O 23 °C                                                                                                                                     |                             | [%]              | 0.45 - 0.50 | 0.40 - 0.45 |
|                                                          | 10 days H <sub>2</sub> O 23 °C                                                                                                                                    |                             | [%]              | 0.70 - 0.80 | 0.65 - 0.70 |
|                                                          | 30 min H <sub>2</sub> O 100 °C                                                                                                                                    |                             | [%]              | 0.55 - 0.60 | 0.45 - 0.50 |
|                                                          | 60 min H <sub>2</sub> O 100 °C                                                                                                                                    |                             | [%]              | 0.70 - 0.80 | 0.60 - 0.70 |
|                                                          |                                                                                                                                                                   |                             |                  |             |             |
| COEFFICIENT OF LINEAR THERMAL EXPANSION<br>(ISO 11359-2) |                                                                                                                                                                   | Mean value:                 | Cure:            | 7 d RT      | 15 h 50 °C  |
|                                                          | $\alpha$ from 20 - 50 °C                                                                                                                                          | [10 <sup>-6</sup> /K]       | 97               | -           | -           |
|                                                          | $\alpha$ from 20 - 90 °C                                                                                                                                          | [10 <sup>-6</sup> /K]       | -                | 71          | -           |
|                                                          | $\alpha$ from 20 - 120 °C                                                                                                                                         | [10 <sup>-6</sup> /K]       | -                | -           | 71          |
|                                                          |                                                                                                                                                                   |                             |                  |             |             |
| POISONS'S RATIO                                          |                                                                                                                                                                   | [v]                         | 0.35             |             |             |

**PROPERTIES OF THE CURED, REINFORCED FORMULATION**
**FLEXURAL TEST**

(ISO 178)

Samples:

 16 layers (4 mm) E-glass fabric 1:1, 280-300 g/m<sup>2</sup>

Fibre volume content: 45 - 46 %

Cure: 10 h 80 °C

*Unconditioned*

|                                 |       |               |
|---------------------------------|-------|---------------|
| Flexural strength               | [MPa] | 440 - 490     |
| Elongation at flexural strength | [%]   | 2.7 - 3.0     |
| Ultimate strength               | [MPa] | 420 - 460     |
| Ultimate elongation             | [%]   | 2.9 - 3.2     |
| Flexural modulus                | [MPa] | 20000 - 22000 |

*After 30 days in H<sub>2</sub>O 23 °C*

|                                 |       |               |
|---------------------------------|-------|---------------|
| Flexural strength               | [MPa] | 380 - 400     |
| Elongation at flexural strength | [%]   | 2.7 - 3.0     |
| Ultimate strength               | [MPa] | 340 - 370     |
| Ultimate elongation             | [%]   | 1.9 - 3.4     |
| Flexural modulus                | [MPa] | 19000 - 21000 |

**TENSILE TEST**

(ISO 527)

Samples:

 16 layers (4 mm) E-glass fabric 1:1, 280-300 g/m<sup>2</sup>

Fibre volume content : 45 - 46 %

Cure: 10 h 80 °C

|                     |       |               |
|---------------------|-------|---------------|
| Tensile strength    | [MPa] | 360 - 390     |
| Ultimate elongation | [%]   | 1.6 - 1.9     |
| Tensile modulus     | [MPa] | 33100 - 39100 |

**INTERLAMINAR  
SHEAR STRENGTH**

(ASTM D 2344)

Short beam: E-glass unidirectional specimen, thickness t = 3.2 mm

Fibre volume content: 60 %

|                                      | <i>Cure:</i> | <i>7 days RT</i> | <i>8 h 80 °C</i> |
|--------------------------------------|--------------|------------------|------------------|
| Unconditioned                        | [MPa]        | 57 - 61          | 60 - 65          |
| After 1 h in H <sub>2</sub> O 100 °C | [MPa]        | 55 - 60          | 58 - 62          |

**HANDLING  
PRECAUTIONS**
**Personal hygiene**
*Safety precautions at workplace*

|                        |                                      |
|------------------------|--------------------------------------|
| protective clothing    | yes                                  |
| gloves                 | essential                            |
| arm protectors         | recommended when skin contact likely |
| goggles/safety glasses | yes                                  |

*Skin protection*

|                      |                                     |
|----------------------|-------------------------------------|
| before starting work | Apply barrier cream to exposed skin |
| after washing        | Apply barrier or nourishing cream   |

*Cleansing of contaminated skin*

Dab off with absorbent paper, wash with warm water and alkali-free soap, then dry with disposable towels.  
Do not use solvents

## Disposal of spillage

Soak up with sawdust or cotton waste and deposit in plastic-lined bin

## Ventilation

of workshop

Renew air 3 to 5 times an hour

of workplaces

Exhaust fans. Operatives should avoid inhaling vapours

## FIRST AID

Contamination of the *eyes* by resin, hardener or mix should be treated immediately by flushing with clean, running water for 10 to 15 minutes. A doctor should then be consulted.

Material smeared or splashed on the *skin* should be dabbed off, and the contaminated area then washed and treated with a cleansing cream (see above). A doctor should be consulted in the event of severe irritation or burns. Contaminated clothing should be changed immediately.

Anyone taken ill after *inhaling* vapours should be moved out of doors immediately.

In all cases of doubt call for medical assistance.

### Huntsman Advanced Materials

(Switzerland) GmbH  
Klybeckstrasse 200  
4057 Basel  
Switzerland

Tel: +41 (0)61 299 11 11

Fax: +41 (0)61 299 11 12

[www.huntsman.com/advanced\\_materials](http://www.huntsman.com/advanced_materials)

Email: [advanced\\_materials@huntsman.com](mailto:advanced_materials@huntsman.com)



Huntsman Advanced Materials warrants only that its products meet the specifications agreed with the user. Specified data are analysed on a regular basis. Data which is described in this document as 'typical' or 'guideline' is not analysed on a regular basis and is given for information purposes only. Data values are not guaranteed or warranted unless if specifically mentioned.

The manufacture of materials is the subject of granted patents and patent applications; freedom to operate patented processes is not implied by this publication. While all the information and recommendations in this publication are, to the best of Huntsman Advanced Material's knowledge, information and belief, accurate at the date of publication, nothing herein is to be construed as a warranty, whether express or implied, including but without limitation, as to merchantability or fitness for a particular purpose. In all cases, it is the responsibility of the user to determine the applicability of such information and recommendations and the suitability of any product for its own particular purpose.

The behaviour of the products referred to in this publication in manufacturing processes and their suitability in any given end-use environment are dependent upon various conditions such as chemical compatibility, temperature, and other variables, which are not known to Huntsman Advanced Materials. It is the responsibility of the user to evaluate the manufacturing circumstances and the final product under actual end-use requirements and to adequately advise and warn purchasers and users thereof.

Products may be toxic and require special precautions in handling. The user should obtain Safety Data Sheets from Huntsman Advanced Materials containing detailed information on toxicity, together with proper shipping, handling and storage procedures, and should comply with all applicable safety and environmental standards.

Hazards, toxicity and behaviour of the products may differ when used with other materials and are dependent on manufacturing circumstances or other processes. Such hazards, toxicity and behaviour should be determined by the user and made known to handlers, processors and end users.

Except where explicitly agreed otherwise, the sale of products referred to in this publication is subject to the general terms and conditions of sale of Huntsman Advanced Materials LLC or of its affiliated companies including without limitation, Huntsman Advanced Materials (Europe) BVBA, Huntsman Advanced Materials Americas Inc., Huntsman Advanced Materials (UAE) FZE, Huntsman Advanced Materials (Guangdong) Company Limited, and Huntsman Advanced Materials (Hong Kong) Ltd.

Huntsman Advanced Materials is an international business unit of Huntsman Corporation. Huntsman Advanced Materials trades through Huntsman affiliated companies in different countries including but not limited to Huntsman Advanced Materials LLC in the USA and Huntsman Advanced Materials (Europe) BVBA in Europe.

All trademarks mentioned are either property of or licensed to Huntsman Corporation or an affiliate thereof in one or more, but not all, countries.

Copyright © 2012 Huntsman Corporation or an affiliate thereof. All rights reserved.