

Fiche Technique

KIMYA PA CARBON 3D FILAMENT

PA/Carbon Fibre additive manufacturing filament

DESCRIPTION

Kimya PA Carbon is a high-performance 3D printing filament made from nylon (polyamide) reinforced with carbon fibres. This engineering-grade thermoplastic offers exceptional mechanical strength, high temperature resistance, and excellent chemical durability. The carbon fiber reinforcement not only improves rigidity but also enhances dimensional stability and reduces warping during printing. With a matte surface finish and ease of use on open-chamber printers, Kimya PA Carbon is ideal for producing strong, heat-resistant parts. Like other nylon-based materials, it should be properly dried before use due to its sensitivity to moisture.

BENEFITS

- High Mechanical Strength.
- Excellent Thermal and Chemical Resistance.
- Low Warpage.

TECHNICAL DATA

Properties

Diameter
 Density
 Melt flow index (MFI)
 Glass transition temperature (Tg)
 Melting Temperature (Tm)

Values

1.75 ± 0.1 mm
 1.192 g/cm³ (0.0431 lb/in³)
 14.5 g/10 min
 71°C (160°F)
 229°C (444°F)

Test Methods

INS-6712
 ISO 1183-1
 ISO 1133-1(@240°C-5kg)
 ISO 11357-1 DSC (10°C/min-20-420°C)
 ISO 11357-1 DSC (10°C/min-20-420°C)

Properties

Heat Distortion Temperature (HDT)
 (1.8Mpa)

Values

120°C (248°F)

Test Methods

ISO 75

Tensile Modulus

10,800 MPa (1566.4 ksi)

ISO 527-2/1A/50

Tensile Strength

127 MPa (18.4 ksi)

ISO 527-2/1A/50

Tensile Strain at Strength

3 %

ISO 527-2/1A/50

Tensile Stress at Break

127 MPa (18.4 ksi)

ISO 527-2/1A/50

Tensile Strain at Break (type A)

3 %

ISO 527-2/1A/50

Flexural Modulus

5,460 MPa (791.9 ksi)

ISO 178

Deformation at Flexural Strain

4 %

ISO 178

Flexural Strength*

177 MPa (25.7 ksi)

ISO 178

Flexural Stress at Break

177 MPa (25.7 ksi)

ISO 178

Deformation at Flexural Strength

4 %

ISO 178

Flexural Stress at Conventional

176 MPa (25.5 ksi)

ISO 178

Deflection (3.5% Strain)*

3.4 kJ/m² (1.6 ft-lbs/in²)

ISO 179-1/1eA

Charpy Impact Resistance

81.3 D

ISO 868

Shore Hardness

PROCESSING

Printing Direction

XY

Printing Speed

40-50 mm/s

Nozzle Temperature

275°C - 285°C (527°F - 545°F)

Bed Temperature

110°C - 120°C (230°F - 248°F)

SUSTAINABILITY



Can be
recycled



Recyclable
packaging

NOTES

- According to ISO 178, end of the test at 5% deformation even if there is no specimen break.
- The data should be considered as indicative values - Properties can be influenced by production conditions.

Dernière mise à jour : 2025-12-22

Nom du chapitre : **KIMYA Filaments for Additive Manufacture**