

Fiche Technique

KIMYA PLA-R 3D FILAMENT

Recycled PLA additive manufacturing filament

DESCRIPTION

Kimya PLA-R is a 3D printing filament made from recycled and biodegradable PLA (Polylactic Acid), a biosourced polymer derived from corn starch. As a natural alternative to petroleum-based plastics like polyethylene, PLA-R is both eco-friendly and easy to print with. It is odorless and well-suited for a wide range of applications—from industrial uses such as packaging to everyday items, toys, prototypes, and modeling. Kimya PLA-R combines printability, sustainability, and versatility, making it a great choice for environmentally conscious 3D printing.

BENEFITS

- Consistent Print Quality
- Low Shrinkage
- Fast Printing Speed

TECHNICAL DATA

Properties

Diameter	1.75 ± 0.1 mm	INS-6712
Density	2.85 ± 0.1 mm	ISO 1183-1
Moisture rate	1.235 g/cm ³	INS-6711
Melt flow index (MFI)	< 0.5 %	ISO 1133-1
Glass transition temperature (Tg)	9-12 g/10min	ISO 11357-1 DSC (10°C/min-20-220°C)
Melting Temperature (Tm)	61°C (142°F)	ISO 11357-1 DSC (10°C/min-20-220°C)

Values

1.75 ± 0.1 mm
2.85 ± 0.1 mm
1.235 g/cm ³
< 0.5 %
9-12 g/10min
61°C (142°F)
165°C (329°F)

Test Methods

INS-6712
ISO 1183-1
INS-6711
ISO 1133-1
ISO 11357-1 DSC (10°C/min-20-220°C)
ISO 11357-1 DSC (10°C/min-20-220°C)

Properties

Tensile Modulus	2,818 MPa (408.7 ksi)	ISO 527-2/5A/50
Tensile Strength	55.32 MPa (8.0 ksi)	ISO 527-2/5A/50
Tensile Strain at Strength	2.1 %	ISO 527-2/5A/50
Tensile Stress at Break	41.2 MPa (6.0 ksi)	ISO 527-2/5A/50
Tensile Strain at Break (type A)	4.32 %	ISO 527-2/5A/50
Flexural Modulus	2,304 MPa (334 ksi)	ISO 178
Flexural Stress at Break	82.3 MPa (11.94 ksi)	ISO 178
Deformation at Flexural Strain	4.22 %	ISO 178
Flexural Stress at Conventional Deflection (3.5% Strain)*	81.72 MPa (11.9 ksi)	ISO 178
Charpy Impact Resistance	3.12 kJ/m ² (1.5 ft-lbs/in ²)	ISO 179-1/1eA
Shore Hardness	75.2 D	ISO 868

Values

2,818 MPa (408.7 ksi)
55.32 MPa (8.0 ksi)
2.1 %
41.2 MPa (6.0 ksi)
4.32 %
2,304 MPa (334 ksi)
82.3 MPa (11.94 ksi)
4.22 %
81.72 MPa (11.9 ksi)
3.12 kJ/m ² (1.5 ft-lbs/in ²)
75.2 D

Test Methods

ISO 527-2/5A/50
ISO 527-2/5A/50
ISO 527-2/5A/50
ISO 527-2/5A/50
ISO 527-2/5A/50
ISO 178
ISO 178
ISO 178
ISO 178
ISO 179-1/1eA
ISO 868

PROCESSING

Printing Direction

Printing Speed
Nozzle Temperature
Bed Temperature

XY

Initial layers: 10-20 mm/s, further layers 30-60 mm/s
190°C - 210°C (374°F - 410°F)
20°C - 60°C (68°F - 140°F)

SUSTAINABILITY



Can be recycled



Contains recycled materials



Made with Bio-based materials



Recyclable packaging



Biodegradable Product

NOTES

- *According to ISO 178, end of the test at 5% deformation even if there is no specimen break.
- The data should be considered as indicative values - Properties can be influenced by production conditions.

Dernière mise à jour : 2025-12-22

Nom du chapitre : **KIMYA Filaments for Additive Manufacture**

As the conditions or methods of use, including storage, are beyond our control, Airtech Europe does not assume any responsibility for the performance of this material for any particular use. The material is sold "as is". Airtech Europe disclaims, and buyer waives, any and all implied warranties, including without limitation the implied warranties of merchantability and of fitness for particular use. The information contained herein represents typical properties and should not be used for specification purposes. This translation is provided for your convenience only. The official language is English and the official law is Luxembourg.