

Advanced Materials**Araldite® LY 3505 / Aradur® 5003-1*****WARM TO HOT CURING EPOXY SYSTEM**

Araldite® LY 3505 is an epoxy resin

Aradur® 5003-1 is a polyamine based hardener

APPLICATIONS	• Industrial composites • Structural composites		
PROPERTIES	The system exhibits excellent mechanical properties and good thermal resistance. Due to its high reactivity short cure cycles can be realized.		
PROCESSING	• Wet lay-up • Resin Transfer Moulding (RTM) • Pressure moulding		
KEY DATA	Araldite® LY 3505		
	Aspect (visual)	clear liquid	
	Colour (Gardner, ISO 4630)	≤ 3	
	Viscosity at 25 °C (ISO 12058-1)	6500 - 8000	[mPa s]
	Density at 25 °C (ISO 1675)	1.15 - 1.20	[g/cm ³]
	Flash point (ISO 2719)	≥ 200	[°C]
	Storage temperature (see expiry date on original container)	2 - 40	[°C]
	Aradur® 5003-1		
	Aspect (visual)	clear light-yellow liquid	
	Viscosity at 25 °C (ISO 12058-1)	70 - 120	[mPa s]
	Density at 25 °C (ISO 1675)	0.98 - 1.08	[g/cm ³]
	Flash point (ISO 2719)	~ 174	[°C]
	Storage temperature (see expiry date on original container)	2 - 40	[°C]
STORAGE	Provided that the products described above are stored in a dry place in their original, properly closed containers at the above mentioned storage temperatures they will have the shelf lives indicated on the labels. Partly emptied containers should be closed immediately after use.		

* In addition to the brand name product denomination may show different appendices , which allows us to differentiate between our production sites:
e.g , BD = Germany, US = United States, IN = India, CI = China, etc.. These appendices are in use on packaging, transport and invoicing documents.
Generally the same specifications apply for all versions. Please address any additional need for clarification to the appropriate Huntsman contact.

PROCESSING DATA

MIX RATIO	<i>Components</i>	<i>Parts by weight</i>	<i>Parts by volume</i>
	Araldite® LY 3505	100	100
	Aradur® 5003-1	20	22

We recommend that the components are weighed with an accurate balance to prevent mixing inaccuracies which can affect the properties of the matrix system. The components should be mixed thoroughly to ensure homogeneity. It is important that the side and the bottom of the vessel are incorporated into the mixing process.

When processing large quantities of mixture the pot life will decrease due to exothermic reaction. It is advisable to divide large mixes into several smaller containers.

INITIAL MIX VISCOSITY (ISO 12058-1)	<i>[°C]</i> at 25	<i>[mPa s]</i> 1800 - 2300
---	----------------------	-------------------------------

POT LIFE (TECAM, 100 ML, 65 % RH)	<i>[°C]</i> at 25	<i>[min]</i> 42 - 56
--	----------------------	-------------------------

GEL TIME (HOT PLATE)	<i>[°C]</i> at 40 at 60 at 80 at 90	<i>[min]</i> 40 - 58 15 - 20 4.5 - 7 2 - 4
--------------------------------	---	--

The values shown are for small amounts of pure resin/hardener mix. In composite structures the gel time can differ significantly from the given values depending on the fibre content and the laminate thickness.

GELATION AT 23 °C (IN THIN LAYERS: 0.4 - 0.7 MM)	Start End	<i>[h]</i> 1.5 - 2 2.5 - 3.5
---	--------------	------------------------------------

TYPICAL CURE CYCLES	30 min 80 °C or 30 min 80 °C + 30 min 100 °C or 30 min 80 °C + 30 min 120 °C
----------------------------	--

The optimum cure cycle has to be determined case by case depending on the processing and the economic requirements.

PROPERTIES OF THE CURED, NEAT FORMULATION

GLASS TRANSITION TEMPERATURE (T_g)		<i>Cure:</i>	T_g [°C]
(IEC 1006, DSC, 10 K/MIN)	4 h 60 °C		77 - 85
	20 min 80 °C		83 - 90
	30 min 80 °C		88 - 95
	2 h 80 °C		95 - 102
	15 min 90 °C		94 - 102
	30 min 90 °C		98 - 106
	1 h 90 °C		100 - 108
	15 min 100 °C		100 - 108
	30 min 80 °C + 30 min 100 °C		106 - 114
	30 min 80 °C + 1 h 100 °C		108 - 118
	30 min 80 °C + 2 h 100 °C		110 - 120
	30 min 80 °C + 1 h 120 °C		120 - 126
	30 min 80 °C + 30 min 140 °C		118 - 126
TENSILE TEST		<i>Cure:</i>	30 min 80 °C + 2 h 100 °C
(ISO 527)	Tensile strength	[MPa]	76 - 90
	Elongation at tensile strength	[%]	3.8 - 4.8
	Ultimate strength	[MPa]	75 - 88
	Ultimate elongation	[%]	3.8 - 5.0
	Tensile modulus	[MPa]	3150 - 3350
FLEXURAL TEST		<i>Cure:</i>	30 min 80 °C + 2 h 100 °C
(ISO 178)	Flexural strength	[MPa]	140 - 150
	Elongation at flexural strength	[%]	6.5 - 7.5
	Ultimate strength	[MPa]	138 - 148
	Ultimate elongation	[%]	7.0 - 8.0
	Flexural modulus	[MPa]	3200 - 3400
FRACTURE PROPERTIES		<i>Cure:</i>	30 min 80 °C + 2 h 100 °C
BEND NOTCH TEST	Fracture toughness K_{1C}	[MPa $\sqrt{m}$]	0.90 - 1.05
	Fracture energy G_{1C}	[J/m ²]	210 - 280
WATER ABSORPTION		<i>Cure:</i>	30 min 80 °C + 2 h 100 °C
(ISO 62)	1 day H ₂ O 23 °C	[%]	0.05 - 0.15
	10 days H ₂ O 23 °C	[%]	0.30 - 0.38

PROPERTIES OF THE CURED, REINFORCED FORMULATION

Flexural test (ISO 178)	Samples: 12 layers E-glass fabric UD (425 g/m ²)		
	Laminate thickness: 3.1 - 3.25 mm		
	Fibre volume content: 61 - 64 %		
	Cure: 30 min 80 °C + 2 h 100 °C		
	Flexural strength	[MPa]	1050 - 1300
	Ultimate elongation	[%]	2.6 - 3.0
	Flexural modulus	[MPa]	38000 - 42000
Interlaminar shear strength (ASTM D 2344)	Short beam: 12 layers E-glass fabric UD (425 g/m ²)		
	Laminate thickness: 3.1 - 3.25 mm		
	Fibre volume content: 61 - 64 %		
	Cure: 30 min 80 °C + 2 h 100 °C		

Shear strength	[MPa]	62 - 68
----------------	-------	---------

**HANDLING
PRECAUTIONS**

Personal hygiene

Safety precautions at workplace

protective clothing	yes
gloves	essential
arm protectors	recommended when skin contact likely
goggles/safety glasses	yes

Skin protection

before starting work	Apply barrier cream to exposed skin
after washing	Apply barrier or nourishing cream

Cleansing of contaminated skin

Dab off with absorbent paper, wash with warm water and alkali-free soap, then dry with disposable towels. Do not use solvents

Disposal of spillage

Soak up with sawdust or cotton waste and deposit in plastic-lined bin

Ventilation

of workshop	Renew air 3 to 5 times an hour
of workplaces	Exhaust fans. Operatives should avoid inhaling vapours

FIRST AID

Contamination of the eyes by resin, hardener or mix should be treated immediately by flushing with clean, running water for 10 to 15 minutes. A doctor should then be consulted.

Material smeared or splashed on the *skin* should be dabbed off, and the contaminated area then washed and treated with a cleansing cream (see above). A doctor should be consulted in the event of severe irritation or burns. Contaminated clothing should be changed immediately.

Anyone taken ill after *inhaling* vapours should be moved out of doors immediately. In all cases of doubt call for medical assistance.

IMPORTANT LEGAL NOTICE

Huntsman Advanced Materials warrants only that its products meet the specifications agreed with the user. Typical properties, where stated, are to be considered as representative of current production and should not be treated as specifications.

The manufacture of materials is the subject of granted patents and patent applications; freedom to operate patented processes is not implied by this publication.

While all the information and recommendations in this publication are, to the best of Huntsman Advanced Material's knowledge, information and belief, accurate at the date of publication, NOTHING HEREIN IS TO BE CONSTRUED AS A WARRANTY, WHETHER EXPRESS OR IMPLIED, INCLUDING BUT WITHOUT LIMITATION, AS TO MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. IN ALL CASES, IT IS THE RESPONSIBILITY OF THE USER TO DETERMINE THE APPLICABILITY OF SUCH INFORMATION AND RECOMMENDATIONS AND THE SUITABILITY OF ANY PRODUCT FOR ITS OWN PARTICULAR PURPOSE.

The behaviour of the products referred to in this publication in manufacturing processes and their suitability in any given end-use environment are dependent upon various conditions such as chemical compatibility, temperature, and other variables, which are not known to Huntsman Advanced Materials. It is the responsibility of the user to evaluate the manufacturing circumstances and the final product under actual end-use requirements and to adequately advise and warn purchasers and users thereof.

Products may be toxic and require special precautions in handling. The user should obtain Safety Data Sheets from Huntsman Advanced Materials containing detailed information on toxicity, together with proper shipping, handling and storage procedures, and should comply with all applicable safety and environmental standards.

Hazards, toxicity and behaviour of the products may differ when used with other materials and are dependent on manufacturing circumstances or other processes. Such hazards, toxicity and behaviour should be determined by the user and made known to handlers, processors and end users.

Except where explicitly agreed otherwise, the sale of products referred to in this publication is subject to the general terms and conditions of sale of Huntsman Advanced Materials LLC or of its affiliated companies including without limitation, Huntsman Advanced Materials (Europe) BVBA, Huntsman Advanced Materials Americas Inc., and Huntsman Advanced Materials (Hong Kong) Ltd.

Huntsman Advanced Materials is an international business unit of Huntsman Corporation. Huntsman Advanced Materials trades through Huntsman affiliated companies in different countries including but not limited to Huntsman Advanced Materials LLC in the USA and Huntsman Advanced Materials (Europe) BVBA in Europe.

Araldite and Aradur are registered trademarks of Huntsman Corporation or an affiliate thereof.

Copyright © 2007 Huntsman Corporation or an affiliate thereof. All rights reserved.

Main Office :
Huntsman Advanced Materials (Switzerland) GmbH
Klybeckstrasse 200
4057 BASEL
Switzerland
+41 61 299 1111