

Fiche Technique

KIMYA PETG CARBON 3D FILAMENT
PETG/Carbon Fibre additive manufacturing filament**DESCRIPTION**

Kimya PETG Carbon is a 3D printing filament made from PETG reinforced with carbon fibres. This combination enhances the mechanical performance of standard PETG by significantly increasing its rigidity and strength. As a result, PETG Carbon is particularly well-suited for producing technical parts that require dimensional stability and durability. It is especially valued in the automotive sector for functional components where performance and precision are key.

BENEFITS

- High rigidity.
- Easy to print.
- Wide range of applications.

TECHNICAL DATA**Properties**

Diameter	1.75 ± 0.1 mm 2.85 ± 0.1 mm
Density	1.28 g/cm ³
Melt flow index (MFI)	6.5 - 10 g/10min
Glass transition temperature (Tg)	78°C (172°F)

Values

1.75 ± 0.1 mm 2.85 ± 0.1 mm
1.28 g/cm ³
6.5 - 10 g/10min
78°C (172°F)

Test Methods

INS-6712
ISO 1183-1
ISO 1133-1 (@225°C-2.16kg)
ISO 11357-1

Properties

Tensile Modulus	7,773.3 MPa (1127.4 ksi)
Tensile Strength	92.9 MPa (13.5 ksi)
Tensile Strain at Strength	1.9 %
Tensile Stress at Break	92.9 MPa (13.5 ksi)
Tensile Strain at Break (type A)	1.9 %
Flexural Modulus	5,664 MPa (821.5 ksi)
Deformation at Flexural Strain	4.2 %
Flexural Strength*	138 MPa (20.0 ksi)
Flexural Stress at Conventional Deflection (3.5% Strain)*	120.6 MPa (17.5 ksi)
Flexural Stress at Break	42.2 MPa (6.1 ksi)
Deformation at Flexural Strength	3.1 %
Charpy Impact Resistance	4.6 kJ/m ² (2.2 ft-lbs/in ²)
Shore Hardness	78.8 D

Values

7,773.3 MPa (1127.4 ksi)
92.9 MPa (13.5 ksi)
1.9 %
92.9 MPa (13.5 ksi)
1.9 %
5,664 MPa (821.5 ksi)
4.2 %
138 MPa (20.0 ksi)
120.6 MPa (17.5 ksi)
42.2 MPa (6.1 ksi)
3.1 %
4.6 kJ/m ² (2.2 ft-lbs/in ²)
78.8 D

Test Methods

ISO 527-2/1A/50
ISO 527-2/1A/50
ISO 527-2/1A/50
ISO 527-2/1A/50
ISO 527-2/1A/50
ISO 178
ISO 178
ISO 178
ISO 178
ISO 178
ISO 178
ISO 179-1/1eA
ISO 868

PROCESSING**Printing Direction**

Printing Speed
Nozzle Temperature
Bed Temperature

XY

Initial layers: 10-20 mm/s, further layers 30-60 mm/s
230°C - 260°C (446°F - 500°F)
85°C - 95°C (185°F - 203°F)

SUSTAINABILITYCan be
recycledRecyclable
packaging**NOTES**

- *According to ISO 178, end of the test at 5% deformation even if there is no specimen break.
- The data should be considered as indicative values - Properties can be influenced by production conditions.

Dernière mise à jour : 2025-12-22

Nom du chapitre : **KIMYA Filaments for Additive Manufacture**

As the conditions or methods of use, including storage, are beyond our control, Airtech Europe does not assume any responsibility for the performance of this material for any particular use. The material is sold "as is". Airtech Europe disclaims, and buyer waives, any and all implied warranties, including without limitation the implied warranties of merchantability and of fitness for particular use. The information contained herein represents typical properties and should not be used for specification purposes. This translation is provided for your convenience only. The official language is English and the official law is Luxembourg.