

BB470 tooling board adhesive is specifically compatible with our range of medium-density polyurethane (PU) tooling boards, for bonding of boards.

COMPATIBILITY

BB470 can be used for bonding of any of the following tooling boards:

- BP600
- BP700
- BP701
- BP750
- BP850

FEATURES & BENEFITS

BB470 provides a high-strength adhesion and offers room temperature curing.

- Colour and density matched to BP700 and BP701
- Good adhesion to a wide range of materials
- Good open life
- High mechanical properties
- Room temperature curing

TECHNICAL PROPERTIES

PROPERTY	VALUE
COLOUR	Brown
HARDNESS, SHORE D (+/- 3), ISO 868	70
RESIN DENSITY, G/CC (+/- 0.3)	0.76
HARDNER DENSITY, G/CC (+/- 0.3)	1.03
GLASS TRANSITION TEMPERATURE (T _g) DSC, POST CURED °C (+/- 5)	100
RESIN VISCOCITY, 50°C, CPS (+/- 300)	1,600
HARDENER VISCOCITY, 50°C, CPS (+/- 60)	220
GEL TIME, 25 °C, 150G MASS, MINUTES (+/- 5)	45
THIN FILM GEL TIME, 25 °C, HOURS	3 - 4
APPROX. COVERAGE PER PACK (SUBSTRATE DEPENDENT, M ² @ 1MM THICKNESS)	7.5
MIX RATIO BY WEIGHT, RESIN : HARDNER	100 : 20
PACK SIZE, PART A, KG	5
PACK SIZE, PART B, KG	1

PACK SIZES

BB470 is a two part adhesive, available in a pack size of 5kg part A and 1kg part B.

STORAGE OF MATERIAL

The product must be stored indoors, on a flat dry surface at a temperature between + 15 °C to + 40 °C. After use, tightly reseal.

The resin component may crystallize during storage. If crystallized, vent container and heat to + 55 °C to + 65 °C until crystals dissolve.

Stir well after product has liquefied.

SHELF LIFE

24 months from date of manufacture.

SUBSTRATE PREPERATION

All surfaces should be free of contamination. Any cleaning solutions must be allowed to evaporate before application of BB470.

USAGE

Always use clean dry tools for mixing and applying.

Mix according to the mix ratio stated above (100:20 by weight).

Mix thoroughly and use immediately.

Material temperatures should not be below + 18°C when mixing.



Base Materials is an expert in high-performance syntactic materials for a wide range of industries including automotive, aerospace, foundry, manufacturing, marine, motorsport, rail and subsea.

Customers are at the heart of what we do. Our proven high-quality solutions are engineered to meet your challenging application requirements.

CONTACT US

+44 (0)116 286 5073

sales@base-materials.com

www.base-materials.com

Disclaimer

The test data and results set forth herein are based on laboratory work and do not necessarily indicate the results that the buyer or user will attain. Base Materials Limited makes no warranty expressed or implied, including warranties of merchantability or fitness for a particular use. Under no circumstances will Base Materials Limited be liable for incidental, consequential or other damages, alleged negligence, breach of warranty, strict liability or any other legal theory arising out of the use or handling of this product.