

Fiche Technique

KIMYA ABS-S 3D FILAMENT

Low-cost filament for FFF 3D Printers

DESCRIPTION

Kimya ABS-S is a 3D printing filament made from ABS (Acrylonitrile Butadiene Styrene), a thermoplastic polymer from the styrenic family. Known for its high impact resistance, rigidity, and low weight, ABS-S is particularly valued for its excellent surface finish and ease of coloring. These properties make it a preferred material for aesthetic, visible parts. Kimya ABS-S is commonly used for outer casings in domestic appliances, telephony, IT equipment, and toys, offering a balance of strength and visual appeal.

BENEFITS

- Rigid.
- Lightweight.
- Colorable.

TECHNICAL DATA**Properties**

Diameter	1.75 ± 0.1 mm	INS-6712
Density	2.85 ± 0.1 mm	ISO 1183-1
Moisture rate	1.035 g/cm ³	INS-6711
Melt flow index (MFI)	< 0.5 %	ISO 1133-1 (@220°C-10kg)
Glass transition temperature (Tg)	3.5 - 6 g/10min	ISO 11357-1 DSC (10°C/min-20-300°C)

Values

1.75 ± 0.1 mm
2.85 ± 0.1 mm
1.035 g/cm ³
< 0.5 %
3.5 - 6 g/10min
107°C (224°F)

Test Methods**Properties**

Tensile Modulus	1,484 MPa (215 ksi)	ISO 527-2/5A/50
Tensile Strength	35.3 MPa (5.1 ksi)	ISO 527-2/5A/50
Tensile Strain at Strength	2.7 %	ISO 527-2/5A/50
Tensile Stress at Break	22.8 MPa (3.3 ksi)	ISO 527-2/5A/50
Tensile Strain at Break (type A)	9.8 %	ISO 527-2/5A/50
Flexural Modulus	1,433 MPa (209.3 ksi)	ISO 178
Deformation at Flexural Strain	> 5 %	ISO 178
Flexural Stress at Conventional Deflection (3.5% Strain)*	43.6 MPa (6.32 ksi)	ISO 178
Charpy Impact Resistance	24.7 kJ/m ² (11.75 ft-lbs/in ²)	ISO 179-1/1eA
Shore Hardness	70 D	ISO 868

Values

1,484 MPa (215 ksi)
35.3 MPa (5.1 ksi)
2.7 %
22.8 MPa (3.3 ksi)
9.8 %
1,433 MPa (209.3 ksi)
> 5 %
43.6 MPa (6.32 ksi)
24.7 kJ/m ² (11.75 ft-lbs/in ²)
70 D

Test Methods

ISO 527-2/5A/50
ISO 527-2/5A/50
ISO 527-2/5A/50
ISO 527-2/5A/50
ISO 527-2/5A/50
ISO 178
ISO 178
ISO 178
ISO 179-1/1eA
ISO 868

PROCESSING**Printing Direction**

Printing Speed
Nozzle Temperature
Bed Temperature

XY

Initial layers: 10-15 mm/s, further layers 20-50 mm/s
255°C - 270°C (491°F - 518°F)
85°C - 95°C (185°F - 203°F)

NOTES

- *According to ISO 178, end of the test at 5% deformation even if there is no specimen break.
- The data should be considered as indicative values - Properties can be influenced by production conditions.