

# XIAMETER® PMX-200 Silicone Fluid, 0.65 - 2 cSt

## Polydimethylsiloxane base fluid

### FEATURES

- Good dielectric properties
- High water repellency
- High shearability without breakdown
- High compressibility
- High spreadability
- Low surface tension
- Low reactivity
- Low vapor pressure
- Good heat stability
- Good leveling and easy rubout
- Essentially odorless
- Soluble in a wide range of solvents
- Volatile carrier
- Compatible with a wide range of cosmetic ingredients

### BENEFITS

For personal care:

- Soft feel and subtle skin lubricity
- Excellent spreading
- Leaves no residue or buildup
- Transient effect
- Nongreasy feel

For industrial applications:

- Little change in physical properties over a wide temperature span – a relatively flat viscosity-temperature slope, and serviceability from -40°C up to 200°C
- Low surface tension – readily wets clean surfaces to impart water repellency and release characteristics

### COMPOSITION

- Polydimethylsiloxane fluid
- Chemical composition  
 $(\text{CH}_3)_3\text{SiO}[\text{SiO}(\text{CH}_3)_2]_n\text{Si}(\text{CH}_3)_3$

### APPLICATIONS

- Personal care products such as hair sprays, cleansing creams, skin creams, lotions, bath oils, suntan products, and nail polishes
- Personal care products such as antiperspirants and deodorants (1 cSt, 1.5 cSt, 2 cSt)
- Industrial applications such as glass vial and lens coatings, household product ingredients, mechanical fluids, penetrating oil ingredients, surface active agents, coatings, electrical insulating fluids and polish ingredients

### DESCRIPTION

XIAMETER® PMX-200 Silicone Fluid is a polydimethylsiloxane fluid commonly used as a base fluid in personal care products due to its excellent spreading and unique volatility characteristics. It is clear, tasteless, essentially odorless and non-greasy. Unlike other volatile carriers used in the personal care industry, this volatile silicone fluid does not cool the skin when it evaporates, a consequence of its unusually low heat of vaporization.

XIAMETER PMX-200 Silicone Fluid, 0.65 cSt, is a volatile fluid with an appreciable vapor pressure at ambient temperature.

Commercial bulk-polymerized dimethyl silicone fluids, such as XIAMETER PMX-200 Silicone Fluids, typically contain trace amounts of impurities.

### HOW TO USE

XIAMETER PMX-200 Silicone Fluid may be used alone or blended with other cosmetic fluids to provide a fluid base for a variety of cosmetic ingredients. It features good solubility in most anhydrous alcohols and in many solvents used in cosmetics.

### PRODUCT SAFETY INFORMATION

XIAMETER PMX-200 Silicone Fluid may cause temporary eye discomfort.

Use caution when handling volatile fluids at temperatures within 10°C of the quoted flash point.

XIAMETER PMX-200 Silicone Fluid with viscosities below 5 cSt are flammable. Keep away from heat, sparks, open flames and other sources of ignition. Keep container tightly closed.

At elevated temperatures, XIAMETER PMX-200 Silicone Fluids are sensitive to contamination by strong acids, bases, some metallic compounds and oxidizing agents. These contaminants may cause an accelerated rate of volatile byproduct formation. Oxidizing agents can also cause an increase in fluid viscosity. When these conditions may exist, it is recommended that the flash point of the fluids be checked periodically to monitor operational safety. Also, ignitable conditions may exist if the fluid is giving off smoke.

## TYPICAL PROPERTIES

Specification Writers: These values are not intended for use in preparing specifications. Please contact your local XIAMETER® sales representative prior to writing specifications on this product.

| Test                                 | Unit               | Value                            |                      |                      |                      |
|--------------------------------------|--------------------|----------------------------------|----------------------|----------------------|----------------------|
|                                      |                    | XIAMETER® PMX-200 Silicone Fluid |                      |                      |                      |
|                                      |                    | 0.65 cSt                         | 1.0 cSt              | 1.5 cSt              | 2.0 cSt              |
| Appearance                           |                    | Crystal clear                    | Crystal clear        | Crystal clear        | Crystal clear        |
| INCI Name                            |                    | Disiloxane                       | Trisiloxane          | Dimethicone          | Dimethicone          |
| Specific Gravity at 25°C (77°F)      |                    | 0.760                            | 0.816                | 0.851                | 0.872                |
| Refractive Index at 25°C (77°F)      |                    | 1.3745                           | 1.3826               | 1.3874               | 1.3904               |
| Color, APHA                          |                    | 5                                | 5                    | 5                    | 5                    |
| Flash Point, Closed Cup              | °C                 | -1                               | 30                   | 57                   | 87                   |
| Acid Number, BCP                     |                    | trace                            | trace                | nil                  | nil                  |
| Melt Point                           | °C <sup>1,2</sup>  | -68                              | -86                  | -76                  | -84                  |
| Pour Point                           | °C                 | -68                              | -100                 | -100                 | -100                 |
| Surface Tension at 25°C (77°F)       | dynes/cm           | 15.9                             | 17.4                 | 18.0                 | 18.7                 |
| Viscosity Temperature Coefficient    |                    | 0.31                             | 0.41                 | 0.46                 | 0.48                 |
| Coefficient of Expansion             | cc/cc/°C           | 0.00134                          | 0.00134              | 0.00134              | 0.00117              |
| Thermal Conductivity at 50°C (122°F) | g cal<br>cm•sec °C | 0.00024                          | —                    | —                    | 0.00026              |
| Solubility Parameter <sup>3</sup>    |                    | 6.8                              | 7.0                  | 7.0                  | 7.1                  |
| Solubility in Typical Solvents       |                    |                                  |                      |                      |                      |
| Chlorinated Solvents                 |                    | High                             | High                 | High                 | High                 |
| Aromatic Solvents                    |                    | High                             | High                 | High                 | High                 |
| Aliphatic Solvents                   |                    | High                             | High                 | High                 | High                 |
| Chlorinated Solvents                 |                    | High                             | High                 | High                 | High                 |
| Dry Alcohols                         |                    | Good                             | Good                 | Good                 | Good                 |
| Water                                |                    | Poor                             | Poor                 | Poor                 | Poor                 |
| Fluorinated Propellants              |                    | High                             | High                 | High                 | High                 |
| Dielectric Strength at 25°C (77°F)   | volts/mil          | 300                              | 350                  | 350                  | 350                  |
| Volume Resistivity at 25°C (77°F)    | ohm-cm             | 1.0x10 <sup>14</sup>             | 1.0x10 <sup>14</sup> | 5.0x10 <sup>14</sup> | 5.0x10 <sup>14</sup> |

<sup>1</sup>The melt point temperature is a typical value and may vary somewhat due to molecular distribution. If the melting point is critical to your application, then several lots should be thoroughly evaluated.

<sup>2</sup>Due to different rates of cooling, this test method may yield pour points lower than the temperature at which these fluids would melt.

<sup>3</sup>Fedors Method: R.F. Fedors, Polymer Engineering and Science, Feb. 1974.

## PRODUCT SAFETY

INFORMATION REQUIRED FOR SAFE USE IS NOT INCLUDED IN THIS DOCUMENT. BEFORE HANDLING, READ PRODUCT AND SAFETY DATA SHEETS AND CONTAINER LABELS FOR SAFE USE, PHYSICAL, ENVIRONMENTAL, AND HEALTH HAZARD INFORMATION. THE SAFETY DATA SHEET IS AVAILABLE ON THE XIAMETER® WEBSITE AT [WWW.XIAMETER.COM](http://WWW.XIAMETER.COM).

## STORAGE

Product should be stored at or below 25°C (77°F) in original, unopened containers. The most up-to-date shelf life information can be found on the XIAMETER website in the Product Detail page under Sales Specification.

## LIMITATIONS

This product is neither tested nor represented as suitable for medical or pharmaceutical uses. Not intended for human injection. Not intended for food use.

## LIMITED WARRANTY INFORMATION – PLEASE READ CAREFULLY

The information contained herein is offered in good faith and is believed to be accurate. However, because conditions and methods of use of our products are beyond our control, this information should not be used in substitution for customer's tests to ensure that our products are safe, effective, and fully satisfactory for the intended end use. Suggestions of use shall not be taken as inducements to infringe any patent.

Dow Corning's sole warranty is that our products will meet the sales specifications in effect at the time of shipment.

Your exclusive remedy for breach of such warranty is limited to refund of purchase price or replacement of any product shown to be other than as warranted.

**TO THE FULLEST EXTENT PERMITTED BY APPLICABLE LAW, DOW CORNING SPECIFICALLY DISCLAIMS ANY OTHER EXPRESS OR IMPLIED WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE OR MERCHANTABILITY.**

**DOW CORNING DISCLAIMS LIABILITY FOR ANY INCIDENTAL OR CONSEQUENTIAL DAMAGES.**