

Fiche Technique

KIMYA PA6-CO 3D FILAMENT

Nylon 6 copolymer additive manufacturing filament

DESCRIPTION

Kimya PA6-CO is a 3D printing filament made from a Nylon 6-based copolymer. This unfilled polyamide stands out for its excellent tensile strength, low warping, and ease of use—even on open-chamber printers. Unlike many other nylon filaments, PA6-CO combines strong mechanical, chemical, and heat resistance with user-friendly printability, making it an ideal standard polyamide for functional parts and industrial applications. As with all polyamides, the filament should be dried before printing to ensure optimal results.

BENEFITS

- Strong and Reliable.
- Low Warping Behavior.
- Chemical and Heat Resistant.

TECHNICAL DATA**Properties**

Diameter	1.75 ± 0.1 mm 2.85 ± 0.1 mm
Density	1.157 g/cm ³ (0.042 lb/in ³)
Glass transition temperature (T _g)	65°C (149°F)
Melting Temperature (T _m)	227°C (440°F)

Values

1.75 ± 0.1 mm 2.85 ± 0.1 mm
1.157 g/cm ³ (0.042 lb/in ³)
65°C (149°F)
227°C (440°F)

Test Methods

INS-6712
ISO 1183-1
ISO 11357-1 DSC (10°C/min-20-300°C)
ISO 11357-1 DSC (10°C/min-0-300°C)

Properties

Tensile Modulus	2,166 MPa (314.2 ksi)
Tensile Strength	56.1 MPa (8.14 ksi)
Tensile Strain at Strength	4.3 %
Tensile Stress at Break	13.4 MPa (1.94 ksi)
Tensile Strain at Break (type A)	< 14 %
Flexural Modulus	2,017 MPa (292.5 ksi)
Deformation at Flexural Strain	< 5 %
Flexural Stress at Conventional Deflection (3.5% Strain)*	65.9 MPa (9.56 ksi)
Charpy Impact Resistance	3.9 kJ/m ² (1.85 ft-lbs/in ²)
Shore Hardness	77.3 D

Values

2,166 MPa (314.2 ksi)
56.1 MPa (8.14 ksi)
4.3 %
13.4 MPa (1.94 ksi)
< 14 %
2,017 MPa (292.5 ksi)
< 5 %
65.9 MPa (9.56 ksi)
3.9 kJ/m ² (1.85 ft-lbs/in ²)
77.3 D

Test Methods

ISO 527-2/1A/50
ISO 527-2/1A/50
ISO 527-2/1A/50
ISO 527-2/1A/50
ISO 527-2/1A/50
ISO 178
ISO 178
ISO 178
ISO 179-1/1eA
ISO 868

PROCESSING**Printing Direction**

Printing Speed	50-60 mm/s
Nozzle Temperature	265°C - 275°C (509°F - 527°F)
Bed Temperature	70°C - 80°C (158°F - 176°F)

XY

50-60 mm/s
265°C - 275°C (509°F - 527°F)
70°C - 80°C (158°F - 176°F)

SUSTAINABILITYCan be
recycledRecyclable
packaging**NOTES**

- *According to ISO 178, end of the test at 5% deformation even if there is no specimen break.
- The data should be considered as indicative values - Properties can be influenced by production conditions.