

*Provisional Technical Data Sheet***Advanced Materials**

Araldite® CW 30407	100	pbw
Aradur® HW 30408	50 • a	pbw
Aradur® HY 30409	9 • (1-a)	pbw

* a can vary between 0 and 1.

High performance resin system for e-motor potting in e-mobility with adaptable heat conductivity and viscosity.

Application Electrical motors and power electronics

Processing methods Automated Pressure Gelation (APG)
(Vacuum) Casting

Key Properties Adaptable thermal conductivity between 0.8 and 1.1 W/(m·K)
Excellent flow and gap filling with adaptable viscosity
Fast processing and curing
Suitable for thermal class 180 (H) applications
Very good thermal shock resistance

Product Data (Guideline Values)

Araldite® CW 30407 (LME 11567-1)

Modified, solvent free epoxy resin with inorganic filler

Appearance	Visual		Anthracite viscous liquid
Viscosity at 60°C, 30s ⁻¹	ISO 3219	mPa·s	3'000 – 8'000*
Specific gravity at 25°C	ISO 2811-3	g/cm ³	2.020 – 2.120*

* Specified Value

Aradur® HW 30408 (LME 11568)

Liquid amine hardener with inorganic filler

Appearance	Visual		White grey viscous paste
Viscosity at 60°C, 30s ⁻¹	ISO 3219	mPa·s	2'300 – 7'000*
Specific gravity at 25°C	ISO 2811-3	g/cm ³	1.940 – 2.070*

* Specified Value

Aradur® HY 30409 (LME 11316)

Liquid amine hardener

Appearance	Visual		Clear transparent liquid
Viscosity at 25°C	ISO 12058	mPa·s	10
Specific gravity at 25°C	ISO 2811-3	g/cm ³	0.95

Processing Data (Guideline Values)

Mix Ratio

	<i>filled</i>	<i>partly-filled</i>	<i>3k-system**</i>
	CW 30407 HW 30408	CW 30407 HY 30409	CW 30407 CW 30408 HY 30409
Parts by weight (pbw)	100 : 50	100 : 9	100 : (50 · a) : 9 · (1-a)
Parts by volume (pbv)	100 : 52	100 : 20	100 : (52 · a) : 20 · (1-a)

** a can vary between 0 and 1.

Gel Time, Viscosity and Curing

			CW 30407 (100 pbw) HW 30408 (50 pbw)	CW 30407 (100 pbw) HY 30409 (9 pbw)
Mix viscosity	ISO 3219			
at 50°C	Rheomat 300 MS DIN	mPa·s	6'500	1'600
at 60°C	125 D=10s ⁻¹	mPa·s	4'500	1'000
Pot life (Time to double initial viscosity)	ISO 3219			
at 50°C	Rheomat 300 MS DIN	min	34	28
at 60°C	125 D=10s ⁻¹	min	21	17
Gel time	ISO 9396			
at 60°C		min	65	95
at 80°C		min	25	31
at 100°C		min	11	11
at 120°C		s	330 – 450*	330 – 450*
Standard cure cycle for test plates			2 h at 120°C	

* Specified Value




Fig.1 Viscosity increase at 50°C and 60°C (Rheomat 300 MS DIN 125 D= 10s-1)

Processing and Storage (Guideline Values)

Preparation

Because of the tendency to sedimentation of the filled resin and hardener in principle require stirring before removal from the original containers. To avoid errors in dosage this step is especially important when removing only part of the contents.

To facilitate stirring and removal, highly filled components are heated to 60 to 80°C in the original container (e.g. overnight in an oven).

Process Parameters APG and Vacuum Casting processes

To prepare the casting mix, the resin component should be homogenized in holding tank A at 60 to 80°C under a vacuum of 1 to 5 mbar, the hardener component in holding tank B at 20 to 50°C and a vacuum of 5 to 10 mbar.

Process	Resin mix temperature	Mold / Part temperature	Demolding time	Cure cycle
APG	50 – 60°C	90 – 120°C	10 – 40 min	Post-Cure: Minimum 1h at 140°C
Vacuum Casting	55 – 70°C	70 – 80°C	-	1h/70°C + 1h/140°C

To determine whether cross-linking has been carried to completion and the final properties are optimal, it is necessary to carry out relevant measurements on the actual object or to measure the glass transition temperature. Different gel and cure cycles in the customer's manufacturing process could lead to a different degree of cross-linking and thus a different glass transition temperature.

Storage Conditions

Store the components in a dry place in tightly sealed original containers. Under these conditions, the shelf life will correspond to the expiry date stated on the label. Partly emptied containers should be tightly closed immediately after use. For information on waste disposal and hazardous products of decomposition in the event of a fire, refer to the Material Safety Data Sheets (MSDS) for these particular products.

Mechanical and Physical Properties (Guideline Values)

Determined on standard test specimen at 23°C. Cured for 2 h at 140°C.

				CW 30407 (100 pbw) HW 30408 (50 pbw)	CW 30407 (100 pbw) HY 30409 (9 pbw)
Color of castings				Dark grey	Dark grey
Glass transition temperature (DSC - midpoint)	ISO 11357	°C	60		65
Density at 28°C	ISO 1183-3	g/cm ³	2.15		2.0
Shore D hardness	ISO 868	-	87		86
Tensile properties at 23°C	ISO 527				
Strength		MPa	55		55
Elongation at break		%	1.5		2.0
E-Modulus		GPa	11		9
Flexural properties at 23°C	ISO 178				
Strength		MPa	110		110
Elongation at break		%	1.2		2.0
E-Modulus		GPa	15		9
Fracture Toughness at 23°C	PM 216-0/89				
Critical stress intensity factor K_{IC}		MPa·√m	4.0		4.0
Specific energy at break G_{IC}		J/m ²	1'000		1'500
Coefficient of linear thermal expansion (CTE below T _g)	ISO 11359-2	ppm/K	20		30
Thermal conductivity	ISO 8894-1	W/(m·K)	1.1		0.8
Water absorption	ISO 62/80				
10 days at 23°C		% by wt.	0.2		0.2
30 min at 100°C		% by wt.	0.2		0.2

Electrical Properties (Guideline Values)

Determined on standard test specimen at 23°C. Cured for 2 h at 140°C.

			CW 30407 (100 pbw) HW 30408 (50 pbw)	CW 30407 (100 pbw) HY 30409 (9 pbw)
Dielectric loss factor ($\tan \delta$, 50Hz, 25°C)	IEC 60250	%	6.0	6.0
Dielectric constant (ϵ_r , 50Hz, 25°C)	IEC 60250	-	6.0	5.8
Volume resistivity (ρ_D , 25°C)	IEC 60093	Ω cm	$2.5 \cdot 10^{14}$	$1.3 \cdot 10^{15}$
Tracking index (CTI)	IEC 60112	grade	>600 – <1 mm	>600 – <1 mm
Dielectric strength (3 mm specimen)	IEC 60243-1	kV/mm	23	23

Legal Notice

Huntsman Advanced Materials

(Switzerland) GmbH
Klybeckstrasse 200
4057 Basel
Switzerland

Tel: +41 (0)61 299 11 11
Fax: +41 (0)61 299 11 12

www.huntsman.com/advanced_materials
Email:
advanced_materials@huntsman.com



Huntsman Advanced Materials warrants only that its products meet the specifications agreed with the user. Specified data are analysed on a regular basis. Data which is described in this document as 'typical' or 'guideline' is not analysed on a regular basis and is given for information purposes only. Data values are not guaranteed or warranted unless if specifically mentioned.

The manufacture of materials is the subject of granted patents and patent applications; freedom to operate patented processes is not implied by this publication. While all the information and recommendations in this publication are, to the best of Huntsman Advanced Material's knowledge, information and belief, accurate at the date of publication, nothing herein is to be construed as a warranty, whether express or implied, including but without limitation, as to merchantability or fitness for a particular purpose. In all cases, it is the responsibility of the user to determine the applicability of such information and recommendations and the suitability of any product for its own particular purpose.

The behaviour of the products referred to in this publication in manufacturing processes and their suitability in any given end-use environment are dependent upon various conditions such as chemical compatibility, temperature, and other variables, which are not known to Huntsman Advanced Materials. It is the responsibility of the user to evaluate the manufacturing circumstances and the final product under actual end-use requirements and to adequately advise and warn purchasers and users thereof.

Products may be toxic and require special precautions in handling. The user should obtain Safety Data Sheets from Huntsman Advanced Materials containing detailed information on toxicity, together with proper shipping, handling and storage procedures, and should comply with all applicable safety and environmental standards.

Hazards, toxicity and behaviour of the products may differ when used with other materials and are dependent on manufacturing circumstances or other processes. Such hazards, toxicity and behaviour should be determined by the user and made known to handlers, processors and end users.

Except where explicitly agreed otherwise, the sale of products referred to in this publication is subject to the general terms and conditions of sale of Huntsman Advanced Materials LLC or of its affiliated companies including without limitation, Huntsman Advanced Materials (Europe) BVBA, Huntsman Advanced Materials Americas Inc., Huntsman Advanced Materials (UAE) FZE, Huntsman Advanced Materials (Guangdong) Company Limited, and Huntsman Advanced Materials (Hong Kong) Ltd.

Huntsman Advanced Materials is an international business unit of Huntsman Corporation. Huntsman Advanced Materials trades through Huntsman affiliated companies in different countries including but not limited to Huntsman Advanced Materials LLC in the USA and Huntsman Advanced Materials (Europe) BVBA in Europe.

All trademarks mentioned are either property of or licensed to Huntsman Corporation or an affiliate thereof in one or more, but not all, countries.

Copyright © 2021 Huntsman Corporation or an affiliate thereof. All rights reserved.