

# 843AR Liquid



## SUPER SHIELD™ Silver Coated Copper Conductive Paint

843AR is a conductive paint that consists of a 1-part, solvent-based acrylic lacquer, pigmented with a highly conductive silver-coated copper flake. It is smooth, hard, and abrasion resistant. It is a ready-to-spray system, with no let down necessary. It has a quick dry time, with no heat cure necessary. It adheres strongly to most injection-molded plastics, such as ABS, PBT, PVA and ABS/PC blend. It provides excellent shielding levels at high frequencies.

843AR is designed to provide a conductive coating for the interior of plastic electronic enclosures that suppresses EMI/RFI emissions. It excels when higher levels of shielding are required.

### Features & Benefits

- UL Recognized (File # E202609)
- Provides effective EMI/RFI shielding over a broad frequency range
- Mild solvent system, safe on polystyrenes
- Does not contain toluene, xylene, or MEK
- Also available in aerosol (843AR-340G) format, see separate TDSs

### Available Packaging

| Cat. No.    | Packaging | Net Vol. | Net Wt. |
|-------------|-----------|----------|---------|
| 843AR-55ML  | Bottle    | 55 mL    | 60 g    |
| 843AR-900ML | Can       | 850 mL   | 927 g   |
| 843AR-3.78L | Can       | 3.60 L   | 3.93 kg |
| 843AR-18.9L | Pail      | 18.9 L   | 20.6 kg |

### Contact Information

MG Chemicals, 1210 Corporate Drive  
Burlington, Ontario, Canada L7L 5R6

Email: [support@mgchemicals.com](mailto:support@mgchemicals.com)

Phone: North America: +(1)800-340-0772

International: +(1) 905-331-1396

Europe: +(44)1663 362888



### Cured Properties

|                                       |                                             |
|---------------------------------------|---------------------------------------------|
| Resistivity                           | $3.0 \times 10^{-4} \Omega \cdot \text{cm}$ |
| Surface Resistance @ 50 $\mu\text{m}$ | 0.080 $\Omega/\text{sq}$                    |
| Service Temperature Range             | -40–120 $^{\circ}\text{C}$                  |

### Usage Parameters

|                                                                     |                                                                |
|---------------------------------------------------------------------|----------------------------------------------------------------|
| Recoat Time                                                         | 3 min                                                          |
| Cure Times                                                          | 24 h @ 22 $^{\circ}\text{C}$<br>30 min @ 65 $^{\circ}\text{C}$ |
| Recommended Film Thickness                                          | 50–65 $\mu\text{m}$                                            |
| Minimum Film Thickness                                              | 30 $\mu\text{m}$                                               |
| Theoretical Coverage @ 2 mil<br>(based on 100% transfer efficiency) | 23 290 $\text{cm}^2/\text{L}$                                  |

### Uncured Properties

|                                   |           |
|-----------------------------------|-----------|
| Viscosity @ 25 $^{\circ}\text{C}$ | <30 cP    |
| Density                           | 1.10 g/mL |
| Percent Solids                    | 31 %      |
| Shelf Life                        | 3 y       |
| Calculated VOC                    | 187 g/L   |

# 843AR Liquid



## Application Instructions

Read the product SDS and Application Guide for more detailed instructions before using this product (downloadable at [www.mgchemicals.com](http://www.mgchemicals.com)).

## Recommended Preparation

Clean the substrate with Isopropyl Alcohol, MG #824, so the surface is free of oils, dust, and other residues.

## Recommended Thinner

843AR is ready to spray. Thinning is not required.

## Brush

Brush application is not recommended for this product. Use a foam brush or MG #855 horse hair brush.


## Manual Spray Guns

Use a standard fluid nozzle gun to spray the diluted paint. The settings listed below are recommendations; however, performance will vary with different brands:

|                     | LVMP       | HVLP       |
|---------------------|------------|------------|
| Nozzle tip diameter | 1.2–1.8 mm | 1.4–1.8 mm |
| Inlet pressure      | 5–15 psi   | 5–15 psi   |
| Air flow            | 10–15 SCFM | 8.3 SCFM   |
| Air cap             | 5–10 psi   | 5–10 psi   |


When using a pressure pot and agitator, keep the agitator at low mixing speed with air pressure of 20–50 psi. Use the lowest pressure necessary to keep the particles suspended.

## Shielding Attenuation



Test performed with a two-coat thickness.

## Surface Resistance by Paint Thickness



## Selective Coating

For higher volume applications, paint can be applied via selective coating equipment. Use a system with constant fluid recirculation to keep the particles from settling in the lines. A fluid nozzle ranging from 1.2 mm–1.8 mm diameter and 5–10 psi fluid pressure is recommended depending on nozzle size.

## Cure Instructions

Allow to dry at room temperature for 24 hours, or after letting sit for 3 minutes, cure the paint in an oven for 30 minutes @ 65 °C.

## Clean-up

Clean spray system and equipment with MEK or acetone, MG # 434.

## Storage and Handling

Store between -5 and 40 °C in a dry area, away from sunlight (see SDS).

## Disclaimer

This information is believed to be accurate. It is intended for professional end-users who have the skills required to evaluate and use the data properly. M.G. Chemicals Ltd. does not guarantee the accuracy of the data and assumes no liability in connection with damages incurred while using it.