

HTCPX

Non-Silicone Heat Transfer Compound Plus - Xtra

HTCPX provides the ultimate in thermal conductivity in a non-curing paste, designed for use as a gap filling material. It is recommended where the efficient and reliable thermal coupling of electronic components or heat dissipation is required. HTCPX is a non-silicone paste, suitable for applications where silicones are prohibited, thus avoiding issues with silicone and low molecular weight siloxane migration.

- Exceptionally high thermal conductivity; aids rapid heat dissipation over uneven surfaces
- Very high viscosity, offering stability under vibration; ideal for use as a gap filling material
- Based on a non-silicone oil; avoids issues with silicone and LMW siloxane migration
- Non-curing paste; allows simple and efficient rework of components if required

Approvals	RoHS Compliant (2015/863/EU):	Yes
Typical Properties	Colour: Base: Thermo-conductive Component: Density @ 20°C (g/ml): Cone Penetration @ 20°C: Viscosity @ 1rpm (Pa s): Thermal Conductivity (Guarded Hot Plate): Thermal Conductivity (Heat Flow): Temperature Range: Weight Loss after 96 hours @ 100°C: Permittivity @ 1GHz: Volume Resistivity: Dielectric Strength:	Pale grey Blend of synthetic fluids Powdered metal oxides 3.1 250 606-670 3.4 W/m.K (calculated) 2.3 W/m.K -50°C to +180°C* <1.0% 4.2 1 x 10 ¹⁴ Ohms-cm 42 kV/mm

*Application dependent; excursions to higher temperatures may be possible, testing in end-use conditions is advised.

<u>Description</u>	<u>Packing</u>	<u>Order Code</u>	<u>Shelf Life</u>
Heat Transfer Compound Plus – Xtra	700 gram cartridge 25 Kg Bulk	HTCPX700G HTCPX25K	36 months 36 months

Copyright Electrolube 2013

All information is given in good faith but without warranty. Properties are given as a guide only and should not be taken as a specification.

Electrolube cannot be held responsible for the performance of its products within any application determined by the customer, who must satisfy themselves as to the suitability of the product.

Ashby Park, Coalfield Way,
 Ashby de la Zouch,
 Leicestershire LE65 1JR
 T +44 (0)1530 419 600
 F +44 (0)1530 416 640
 BS EN ISO 9001:2008
 Certificate No. FM 32082

Directions for Use

HTCPX was developed as a thermally conductive gap filler. For gap filling applications the material can be dispensed either manually or via automated equipment into the desired location. The product should be tested to ensure the thickness of paste applied is suitable for the end application conditions. It should be noted that the thermally conductive pastes are just one layer in the system; dissipation from the heat generating source is achieved through many layers of different material before the heat is dissipated by free or forced convection. Therefore, a thermal paste will only aid the dissipation of heat if the interface where it is used has the lowest thermal conductivity within the system, i.e. is the rate determining step. The use of excess thermal paste will not offer an increase in the efficiency of heat transfer.

For other applications, HTCPX should be applied in the most appropriate manner for the application, avoiding any air inclusion and ensuring the product applied is as uniform as possible. A lower viscosity version of HTCPX is available if required (HTCPX-LV).

Additional Information

There are many methods of measuring thermal conductivity, resulting in large variances in results. Electrolube utilise a heat flow method which takes into account the surface resistance of the test substrate, thus offering highly accurate results of true thermal conductivity. Some alternative methods do not account for such surface resistance and can create the illusion of higher thermal conductivity. Therefore, when comparing thermal conductivity measurements it is important to know what test method has been utilised. For more information please contact the Electrolube Technical Department.

The rate at which heat flows is dependent on the temperature differential, the thickness and uniformity of the layer, and the thermal conductivity of the material. Products with the same comparable thermal conductivity value may have very different efficiencies of heat transfer in the end application depending on how successfully a thin even film can be applied.

A full range of heat transfer products are available from Electrolube: standard and high thermal conductivity pastes (HTC, HTCP), silicone based pastes for very high temperature applications (HTS), Silicone RTVs (TCOR, TCER), epoxy adhesives (TBS) and encapsulation resins (ER2220, UR5633, SC2003).

Bulk Packaging Specifications

Package Size	Diameter	Height
700g Cartridge	49.6mm	260mm + 15mm for Nozzle
25Kg Bulk Container	300mm	285mm

Revision 6: April 2020

Copyright Electrolube 2013

All information is given in good faith but without warranty. Properties are given as a guide only and should not be taken as a specification.

Electrolube cannot be held responsible for the performance of its products within any application determined by the customer, who must satisfy themselves as to the suitability of the product.

Ashby Park, Coalfield Way,
Ashby de la Zouch,
Leicestershire LE65 1JR
T +44 (0)1530 419 600
F +44 (0)1530 416 640
BS EN ISO 9001:2008
Certificate No. FM 32082