

Fiche Technique

KIMYA PA6-CO 3D FILAMENT

Nylon 6 copolymer additive manufacturing filament

DESCRIPTION

Kimya PA6-CO is a 3D printing filament made from a Nylon 6-based copolymer. This unfilled polyamide stands out for its excellent tensile strength, low warping, and ease of use—even on open-chamber printers. Unlike many other nylon filaments, PA6-CO combines strong mechanical, chemical, and heat resistance with user-friendly printability, making it an ideal standard polyamide for functional parts and industrial applications. As with all polyamides, the filament should be dried before printing to ensure optimal results.

BENEFITS

- Strong and Reliable.
- Low Warping Behavior.
- Chemical and Heat Resistant.

TECHNICAL DATA

Properties

Diameter	1.75 ± 0.1 mm 2.85 ± 0.1 mm
Density	1.157 g/cm ³ (0.042 lb/in ³)
Glass transition temperature (T _g)	65°C (149°F)
Melting Temperature (T _m)	227°C (440°F)

Values

1.75 ± 0.1 mm
2.85 ± 0.1 mm
1.157 g/cm ³ (0.042 lb/in ³)
65°C (149°F)
227°C (440°F)

Test Methods

INS-6712
ISO 1183-1
ISO 11357-1 DSC (10°C/min-20-300°C)
ISO 11357-1 DSC (10°C/min-0-300°C)

Properties

Tensile Modulus	2,166 MPa (314.2 ksi)
Tensile Strength	56.1 MPa (8.14 ksi)
Tensile Strain at Strength	4.3 %
Tensile Stress at Break	13.4 MPa (1.94 ksi)
Tensile Strain at Break (type A)	< 14 %
Flexural Modulus	2,017 MPa (292.5 ksi)
Deformation at Flexural Strain	< 5 %
Flexural Stress at Conventional Deflection (3.5% Strain)*	65.9 MPa (9.56 ksi)
Charpy Impact Resistance	3.9 kJ/m ² (1.85 ft-lbs/in ²)
Shore Hardness	77.3 D

Values

2,166 MPa (314.2 ksi)
56.1 MPa (8.14 ksi)
4.3 %
13.4 MPa (1.94 ksi)
< 14 %
2,017 MPa (292.5 ksi)
< 5 %
65.9 MPa (9.56 ksi)
3.9 kJ/m ² (1.85 ft-lbs/in ²)
77.3 D

Test Methods

ISO 527-2/1A/50
ISO 527-2/1A/50
ISO 527-2/1A/50
ISO 527-2/1A/50
ISO 527-2/1A/50
ISO 178
ISO 178
ISO 178
ISO 179-1/1eA
ISO 868

PROCESSING

Printing Direction

Printing Speed	50-60 mm/s
Nozzle Temperature	265°C - 275°C (509°F - 527°F)
Bed Temperature	70°C - 80°C (158°F - 176°F)

XY

50-60 mm/s
265°C - 275°C (509°F - 527°F)
70°C - 80°C (158°F - 176°F)

SUSTAINABILITY



Can be recycled



Recyclable packaging

NOTES

- *According to ISO 178, end of the test at 5% deformation even if there is no specimen break.
- The data should be considered as indicative values - Properties can be influenced by production conditions.

Dernière mise à jour : 2025-12-22

Nom du chapitre : **KIMYA Filaments for Additive Manufacture**

As the conditions or methods of use, including storage, are beyond our control, Airtech Europe does not assume any responsibility for the performance of this material for any particular use. The material is sold "as is". Airtech Europe disclaims, and buyer waives, any and all implied warranties, including without limitation the implied warranties of merchantability and of fitness for particular use. The information contained herein represents typical properties and should not be used for specification purposes. This translation is provided for your convenience only. The official language is English and the official law is Luxembourg.