



## Technical Data Sheet

### DOWSIL™ PV-7326 Potting Agent

Potting material offering thermal management and protection from environmental elements for photovoltaic (PV) junction boxes

#### Features & Benefits

- Tailor made product for PV J-box potting
- Good electrical insulation
- Good heat dissipation with a thermal conductivity of  $>0.5$  W/mk
- Good adhesion performance to J-box substrate without the use of a primer
- Compatible with most frame and adhesive sealants
- UL 94 V0 rated
- Neutral alkoxy silicone sealant
- Fast room temperature cure

#### Composition

- Two-part, 6:1 (by weight) mix ratio silicone elastomer supplied as flowable liquid

#### Applications

- Potting of solar module junction boxes

#### Typical Properties

Specification Writers: These values are not intended for use in preparing specifications.

| CTM <sup>1</sup> | Properties       | Unit       | Result      |
|------------------|------------------|------------|-------------|
| <b>Catalyst</b>  |                  |            |             |
| 0176             | Color            |            | Translucent |
| 0050             | Viscosity        | centipoise | 210         |
| 0097B            | Specific Gravity |            | 0.94        |
| <b>Base</b>      |                  |            |             |
| 0176             | Color            |            | White       |
| 0050             | Viscosity        | centipoise | 4842        |
| 0097B            | Specific Gravity |            | 1.48        |

1. CTMs (Corporate Test Methods) correspond to standard ASTM tests in most instances. Copies of CTMs are available upon request.

## Typical Properties (Cont.)

| CTM               | Properties                              | Unit              | Result    |
|-------------------|-----------------------------------------|-------------------|-----------|
| <b>Mixed</b>      |                                         |                   |           |
| 0176              | Color                                   |                   | White     |
| 0050              | Viscosity Mixed                         | centipoise        | 3300      |
| 0099              | Durometer, Shore A                      |                   | 37        |
| 0022              | Density <sup>2</sup>                    | g/cm <sup>3</sup> | 1.42      |
| 0055              | Working Time <sup>3</sup>               | minutes           | 7.6       |
| 0092              | Non-flow Time                           | minutes           | 38        |
|                   | Room Temperature Cure Time <sup>4</sup> | hours             | 75 @ 25°C |
| 0114              | Dielectric Strength                     | kV/mm             | 25.25     |
| 0249              | Volume Resistance                       | Ω.cm              | 1.08E+15  |
|                   | Thermal Conductivity                    | watts/meter °K    | 0.54      |
| <b>UL Ratings</b> |                                         |                   |           |
| UL 94             | Flame resistance                        |                   | V0        |

2. Cured.
3. Pot life, time to double initial viscosity (initial mixed viscosity for two-part products) at room temperature.
4. Cured at 25°C and 50% RH.

## Description

DOWSIL™ PV-7326 Potting Agent is supplied as two-part liquid component kits comprised of base and catalyst to be mixed in a 6:1 ratio by weight OR 4:1 ratio by volume. It is suitable for manual mixing or automated mixing and dispensing. When liquid components are thoroughly mixed, the mixture cures to a flexible elastomer.

## How to Use

### Substrate Preparation

All surfaces must be clean and dry. Degrease and wash off any contaminants that could impair adhesion.

DOWSIL™ PV-7326 Potting Agent is supplied in two parts that are mixed in a 6:1 ratio by weight OR 4:1 ratio by volume (base and catalyst).

Both base and catalyst part are moisture sensitive. Please keep opened packaging away from moisture. Catalyst is especially very sensitive to moisture. Purging with dry N<sub>2</sub> is suggested when reopening packaging.

DOWSIL™ PV-7326 Potting Agent can be dispensed manually or by using one of the available types of meter mix equipment. Typically, the components are readily mixed with static or dynamic mixers. Automated meter-mix equipment is normally used with high-volume processes. For low-volume applications, manual weighing and simple hand mixing may be appropriate.

Inaccurate proportioning or inadequate mixing may cause localized or widespread problems affecting the pottant properties or cure characteristics. If possible, the potential for air entrapment should be considered during design of the part and selection of a process to mix and dispense the pottant. Subjecting the pottant part to >28 inches Hg vacuum may be necessary to ensure a void-free, protective layer.

## **How to Use (Cont.)**

It is expected that some settling may occur in the base over time. Therefore, it is recommended that the base be mixed in a pail or drum roller before use and for automated line use, it is recommended that the base be applied from an agitated dispense tank.

It is recommended that the material be mixed, such as with a pail or drum roller upon receipt. The material should then be applied from an agitated dispensing tank.

### **Working Time and Cure**

Working time (or pot life) is the time required for the initial mixed viscosity to double at room temperature (RT). For two-part, condensation cure products, such as DOWSIL™ PV-7326 Potting Agent, the cure reaction begins when the catalyst and base are mixed. As the cure progresses, viscosity increases until the material cures. DOWSIL™ PV-7326 Potting Agent will cure at room temperature, 50% relative humidity and the result is 72 hours.

### **Clean Up**

Extra product can be wiped up with a clean cloth before curing. If the product is cured, mechanical removal can be used.

## **Useful Temperature Ranges**

For most uses, DOWSIL™ PV-7326 Potting Agent should be operational over a temperature range of -45 to 150°C (-49 to 302°F) for long periods.

## **Handling Precautions**

PRODUCT SAFETY INFORMATION REQUIRED FOR SAFE USE IS NOT INCLUDED IN THIS DOCUMENT. BEFORE HANDLING, READ PRODUCT AND SAFETY DATA SHEETS AND CONTAINER LABELS FOR SAFE USE, PHYSICAL AND HEALTH HAZARD INFORMATION. THE SAFETY DATA SHEET IS AVAILABLE ON THE DOW WEBSITE AT DOW.COM, OR FROM YOUR DOW SALES APPLICATION ENGINEER, OR DISTRIBUTOR, OR BY CALLING DOW CUSTOMER SERVICE.

## **Usable Life and Storage**

When stored at or below 35°C (95°F) in the original unopened containers, DOWSIL™ PV-7326 Potting Agent has a usable life of 12 months from the date of manufacture.

Storage conditions and shelf life ("Use By" date) are indicated on the product label.

## **Packaging Information**

DOWSIL™ PV-7326 Potting Agent is available in standard pail and drum packaging. Detailed container size information may be obtained from your Dow representative.

## **Limitations**

This product is neither tested nor represented as suitable for medical or pharmaceutical uses.

## **Health and Environmental Information**

To support customers in their product safety needs, Dow has an extensive Product Stewardship organization and a team of product safety and regulatory compliance specialists available in each area.

For further information, please see our website, [dow.com](http://dow.com) or consult your local Dow representative.

## **Disposal Considerations**

Dispose in accordance with all local, state (provincial) and federal regulations. Empty containers may contain hazardous residues. This material and its container must be disposed in a safe and legal manner.

It is the user's responsibility to verify that treatment and disposal procedures comply with local, state (provincial) and federal regulations. Contact your Dow Technical Representative for more information.

## **Product Stewardship**

Dow has a fundamental concern for all who make, distribute, and use its products, and for the environment in which we live. This concern is the basis for our product stewardship philosophy by which we assess the safety, health, and environmental information on our products and then take appropriate steps to protect employee and public health and our environment. The success of our product stewardship program rests with each and every individual involved with Dow products - from the initial concept and research, to manufacture, use, sale, disposal, and recycle of each product.

## **Customer Notice**

Dow strongly encourages its customers to review both their manufacturing processes and their applications of Dow products from the standpoint of human health and environmental quality to ensure that Dow products are not used in ways for which they are not intended or tested. Dow personnel are available to answer your questions and to provide reasonable technical support. Dow product literature, including safety data sheets, should be consulted prior to use of Dow products. Current safety data sheets are available from Dow.

dow.com

**NOTICE:** No freedom from infringement of any patent owned by Dow or others is to be inferred. Because use conditions and applicable laws may differ from one location to another and may change with time, Customer is responsible for determining whether products and the information in this document are appropriate for Customer's use and for ensuring that Customer's workplace and disposal practices are in compliance with applicable laws and other government enactments. The product shown in this literature may not be available for sale and/or available in all geographies where Dow is represented. The claims made may not have been approved for use in all countries. Dow assumes no obligation or liability for the information in this document. References to "Dow" or the "Company" mean the Dow legal entity selling the products to Customer unless otherwise expressly noted. NO WARRANTIES ARE GIVEN; ALL IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE ARE EXPRESSLY EXCLUDED.

