



# Krytox™ XHT

## Performance Lubricants

### Extreme High Temperature Oils


## Product Information

Krytox™ XHT series oils are special extreme high temperature grade oils with low evaporation and extra treatment to allow use at temperatures above the range of normal perfluoropolyether (PFPE) oils. These oils provide excellent lubrication over a broad temperature range. Krytox™ XHT series oils are nonflammable and chemically inert.

Krytox™ XHT oils allow extended lubrication intervals and longer equipment life. The oil can begin to slowly evaporate at temperatures above 330 °C (626 °F), and this will occur at an increasing rate as temperatures increase. Re-lubrication could be required at these temperatures to achieve optimum life.

#### Krytox™ PFPE Oils

Krytox™ PFPE oils are clear, colorless, fluorinated synthetic oils that are nonreactive, nonflammable, safe in chemical and oxygen service, and long lasting. Krytox™ is a PFPE—also called perfluoroalkylether (PFAE) or perfluoropolyalkylether (PFPAE)—with the following chemical structure:



where n=10 to 60

#### Compatibility with Metals

Due to their low surface tensions, Krytox™ oils easily wet metallic surfaces, and, because of their inertness, Krytox™ oils have little or no adverse effect on metals. Testing of metals at 340 °C (644 °F) in the absence of air has shown little evidence of corrosion. In the presence of air, corrosion was slightly higher. The presence of molybdenum in the metals improved corrosion resistance.

**Typical Properties of Krytox™ XHT PFPE Oil\***

|                                 | XHT-500 (H-1)           | XHT-750                  | XHT-1000                 |
|---------------------------------|-------------------------|--------------------------|--------------------------|
| Estimated Useful Range, °C (°F) | -20/300 (-4/572)        | -15/350 (5/662)          | -5/360 (23/680)          |
| Base Oil Viscosity, cSt         |                         |                          |                          |
| 20 °C (68 °F)                   | 1,712                   | 2,610                    | 3,500                    |
| 40 °C (104 °F)                  | 500                     | 738                      | 1,023                    |
| 100 °C (212 °F)                 | 46.4                    | 64.6                     | 88.5                     |
| Oil Viscosity Index             | 148                     | 157                      | 171                      |
| Oil Pour Point, °C (°F)         | -25 (-13)               | -15 (5)                  | -5 (23)                  |
| Oil Density, g/mL               |                         |                          |                          |
| 0 °C (32 °F)                    | 1.95                    | 1.95                     | 1.95                     |
| 100 °C (212 °F)                 | 1.78                    | 1.78                     | 1.78                     |
| Oil Volatility, % in 22 hr      |                         |                          |                          |
| 204 °C (400 °F)                 | <1                      | —                        | —                        |
| 260 °C (500 °F)                 | 0.8                     | 0.6                      | 0.5                      |
| Vapor Pressure                  |                         |                          |                          |
| 20 °C (68 °F) (Knudsen)         | $\leq 1 \times 10^{-9}$ | $\leq 3 \times 10^{-14}$ | $\leq 4 \times 10^{-15}$ |
| 100 °C (212 °F) (Knudsen)       | $\leq 8 \times 10^{-7}$ | $\leq 1 \times 10^{-9}$  | $\leq 2 \times 10^{-10}$ |
| 200 °C (392 °F) (Knudsen)       | $\leq 1 \times 10^{-4}$ | $\leq 2 \times 10^{-6}$  | $\leq 3 \times 10^{-7}$  |
| Food Contact Approval           | NSF H-1                 | None                     | None                     |

\* This table gives typical properties (not specifications) based on historical production performance. Chemours does not make any express or implied warranty that these products will continue to have these typical properties.

The information set forth herein is furnished free of charge and based on technical data that Chemours believes to be reliable. It is intended for use by persons having technical skill, at their own discretion and risk. The handling precaution information contained herein is given with the understanding that those using it will satisfy themselves that their particular conditions of use present no health or safety hazards. Because conditions of product use are outside our control, Chemours makes no warranties, express or implied, and assumes no liability in connection with any use of this information. As with any material, evaluation of any compound under end-use conditions prior to specification is essential. Nothing herein is to be taken as a license to operate under or a recommendation to infringe any patents.

NO PART OF THIS MATERIAL MAY BE REPRODUCED, STORED IN A RETRIEVAL SYSTEM OR TRANSMITTED IN ANY FORM OR BY ANY MEANS ELECTRONIC, MECHANICAL, PHOTOCOPYING, RECORDING OR OTHERWISE WITHOUT THE PRIOR WRITTEN PERMISSION OF CHEMOURS.

For product information, industry applications, technical assistance, or global distributor contacts, visit [krytox.com](http://krytox.com) or within the U.S. and Canada, call 1-844-773-CHEM/2436 or outside of the U.S., call 1-302-773-1000.

© 2016 The Chemours Company FC, LLC. Krytox™ and any associated logos are trademarks or copyrights of The Chemours Company FC, LLC. Chemours™ and the Chemours Logo are trademarks of The Chemours Company.

Replaces: K-02034-5  
C-10879 (6/16)