



Floor Patch™

Description:	All-purpose concrete patching compound that bonds to concrete, brick, masonry, metal, or wood surfaces.		
Intended Use:	Industrial Use: Ideal for patching concrete, brick, masonry, floors, or retaining walls where the concrete has spalled. The material will also bond to wood and metal. Can be used to anchor bolts in concrete.		
Features:	Easy to mix and apply Trowelable to 1/4" or more High compressive strength Resistant to water, oils, solvents, and alkalis		
Limitations:	Suitability of product is determined by the end user for their application and process.		
Typical	Technical data should be considered representative or typical only and should not be used for specification purposes.		
Physical	Cured 7 Days @ 75°F (24°C)	Typical Values	Standard Tests
Properties:	Compressive Strength	8000 psi (55 MPa)	Compressive Strength ASTM D 695
	Hardness	85 Shore D	Hardness, Shore D ASTM D2240
	Solids by Volume	100%	
	Temperature Resistance	Dry: 250°F (121°C); Wet: 120°F (49°C)	
	Uncured Properties @ 72°F (23°C)		
	Application Temperature	60 - 90°F (16 - 32°C)	
	Color	Light Grey	
	Coverage (1/4" / 6.35mm)	60 in2/lb (855 cm2/Kg)	
	Functional Cure @ 75°F (24°C)	16 hours	
	Minimum Recoat Time @ 75F (24°C)	6 - 8 hrs.	
	Mix Ratio Resin/Hardener	5.5:1 weight. 4.5:1 volume	
	Mix Ratio Aggregate/Liquid Ratio	6.67:1 by weight	
	Mixed Viscosity	Putty - Paste	
	Pot Life @ 75F (24°C)	45 min.	
Surface	Concrete & Masonry: Begin with a sound, clean, dry and roughened, oil-free application surface, as it is essential to the success and performance of this product. For proper surface preparation, refer to Concrete or Masonry Surface Preparation as detailed by: SSP/NACE SSPC-SP13/NACE 6 , or ICRI No. 310.2R, CSP 3-5 . for proper surface preparation guidelines.		
Preparation:	Atmospheric: SSPC-SP13/NACE 6, or ICRI No. 310.2R, CSP 3-5 Immersion: SSPC-SP13/NACE 6-4.3.1 or 4.3.2 or ICRI No. 310.2R, CSP 3-5 NEW POURED CONCRETE, allow to fully cure (28 days @ 70°F (21°C)) prior to application. Remove any curing membrane by sanding or etching with a strong detergent. Remove any laitance if present. OLD CONCRETE, thoroughly clean surface with a grease-cutting detergent to remove grease and oils, and remove any loose or unsound concrete by chipping, scarifying, shotblasting, sanding, or grinding. Proceed as for new poured concrete. PREVIOUSLY COATED CONCRETE, applications should be considered short term because the coating system is only as strong as its weakest component. Remove any peeling or degraded paint by sanding or using a paint stripper. For intact paint, thoroughly clean the surface with a strong detergent, then lightly sand to remove any gloss. Treat any areas worn down to the original concrete as bare concrete. Metal: If metal is also being coated, Primer is required . It is recommended to use a wire brush or sandpaper to remover rust and scale from the surface to be protected. Surfaces may be shot blasted or abraded using a wire wheel for best results. All dirt, grease and old paint should be removed. A clean dry surface is essential for the best results. A metal primer is required and is sold separately. See SSPC-SP1 or SSPC-SP10/Nace2 for metal cleaning. Optimal profile 2 mils / 50 microns Atmospheric: SSPC-SP6/NACE 3, ISO 8501-1 SA2 ,2 mil (50 micron) profile Immersion: SSPC-SP10/NACE 2, ISO 8501-1 SA2.5, 2-3 mil (50-75 micron) profile		
Mixing	---- Adequate ventilation is necessary when mixing this product.----		
Instructions:	Mix the liquids (Resin + Hardener) in its totality for 2 minutes. From the mixed liquids put aside around 15% of weight to be used as a primer. (40lb. - 408g/0.90lb.); (10lb. - 102g/0.23lb.) Please be aware that the pot life of the primer is fast and should not last more than 15 minutes at room temperature . The remaining of the liquids should be mixed with the aggregate. Using a Jiffy Mixer HS thoroughly mix the liquids and the aggregate making sure to scrape the edges.		

Application Instructions:

Using a brush or a roller, apply the primer over the application area.
Spread Floor Patch™ over the primed area with a trowel. Spread back and forth to create the top layer. To produce smooth finish, trowel again once product has thickened.

FOR A TRULY SMOOTH FINISH

Dip trowel in water before each application to lessen build-up on trowel and break surface tension of epoxy. DO NOT pour water onto uncured epoxy.

Storage:

Shelf life 3 yrs from manufacture. See package label. Store at room temperature, 70 °F (21°C)

Compliances:

Approved in the U.S. for use in meat and poultry processing plants.
Accepted by Canadian Department of Agriculture Food Safety Service.

Chemical**Resistance:**

Chemical resistance is calculated with a 7-day, room temp. cure (30 days immersion) @ 75°F(24°C).

Ammonia	Very good	Toluene	Poor
Chlorinated Solvent	Very good		
Hydrochloric 10%	Very good		
Kerosene	Fair		
Perchloroethylene	Fair		
Sodium Hydroxide 10%	Very good		
Sulfuric 10%	Very good		

Precautions:

FOR INDUSTRIAL USE ONLY: Please refer to the appropriate Safety Data Sheet prior to using this product.

Warranty:

ITW Performance Polymers will replace any material found to be defective. Because the storage, handling and application of this material is beyond our control, we can accept no liability for the results obtained.

Order**Information:**

<u>Item No.</u>	<u>Package Size</u>
13100	10 lb.
13120	40 lb.

Contacts:

www.itwpp.com

ITW Performance Polymers (EMEA)
Bay 150, Shannon Industrial Estate
Shannon, County Clare, Ireland V14 DF82
TEL: +353 61 771 500
FAX: +353 61 471 285
Email: customerservice.shannon@itwpp.com

ITW Performance Polymers (US)
30 Endicott Street
Danvers, MA 01923 USA
TEL: 855 489 7262
FAX: 978 774 0516
Email: info@itwpp.com

Disclaimer:

Product Use: The information herein is based upon good faith testing that ITW PP believes are reliable, but the accuracy or completeness of such information is not guaranteed. Many factors beyond ITW PP control and uniquely within user's knowledge and control can affect the use and performance of an ITW PP product in a particular application. Given the variety of influencers on performance, the data here is not intended to substitute end user testing. It is the end users sole responsible for evaluating any ITW PP product and determining whether it is fit for a particular purpose and suitable for user's design, production, and final application.

Exclusion of Warranties: As to the herein described materials and test results, there are no warranties which extend beyond the description on the face hereof. ITW PP makes no other warranties, express or implied, including, but not limited to, any implied warranty of merchantability or fitness for a particular purpose. Since the use of the herein described involves many variables in methods of application, design, handling and/or use, the user, in accepting and using these materials, assumes all responsibility for the end result. ITW PP shall not otherwise be liable for loss of damages, whether direct, indirect, special, incidental, or consequential, regardless of the legal theory asserted, including negligence, warranty, or strict liability.