

Data Sheet

WRIGHTLON® 3700

Low cost release film for commercial and wind energy applications

DESCRIPTION

Wrightlon® 3700 is a release film that is designed for low cost applications. Wrightlon® 3700 will release from epoxy, polyester and vinyl ester resin systems.

BENEFITS

- Good value for low to medium temperature applications.
- Blue colour is visible on laminate surface.
- Available in P16 perforation style, especially for infusion applications.

TECHNICAL DATA

		Test method
Material type	Polyolefin	
Elongation at break	500 %	ASTM D882
Tensile strength	30 MPa (4350 psi)	ASTM D882
Maximum use temperature	121°C (250°F)	
Materials to avoid	Phenolic resins/Strong oxidizers	
Colour	Blue	
Storage	Recommended storage temperature is 5°C to 40°C (41°F to 104°F). Store indoors in original packaging, do not stack rolls on end.	

SIZES

Thickness	Width	Forms Available*
25 µm (0.001 inch)	up to 2 m (80 inches)	SHT
33 µm (0.0013 inch)	up to 2 m (80 inches)	SHT
50 µm (0.002 inch)	up to 2 m (80 inches)	SHT

- For more sizes, see the *Commonly Used Sizes* chart in this section.
- Custom shapes and sizes are available, please contact Airtech for more information.

* SHT = sheeting

SUSTAINABILITY



Can be
recycled



Recyclable
packaging

NOTES

- The maximum use temperature is dependent upon the duration at maximum temperature and is process specific, Airtech recommends testing prior to use.
- Watch a demo video of Wrightlon® 3700 in the "Media Centre" on our website.