AIRTECH EUROPE SARL
18, ZI Haneboesch
L-4562 Differdange
LUXEMBOURG
Phone: +352 58 22 82 1
Fax: + 352 58 49 35
E-mail: sales@airtech.lu
Website: www.airtech.lu

Fiche Technique

KIMYA PEBA-S 3D FILAMENT

Flexible and high-elongation filament for FFF 3D printers

DESCRIPTION

Kimya PEBA-S is a 3D printing filament made from PEBA (Polyether Block Amide), a thermoplastic elastomer known for its exceptional flexibility and energy return. Produced through the polycondensation of a polyamide and a polyether, PEBA-S stands out with an elongation at break greater than 550%, making it the most flexible material in the Kimya range. Its elasticity and rebound properties make it ideal for sports equipment and impact-absorbing parts.

BENEFITS

- Flexible.
- Great Impact resistance.
- Lightweight.

TECHNICAL DATA

Properties	Values	Test Methods
Diameter	1.75 ± 0.1 mm 2.85 ± 0.1 mm	INS-6712
Density	1.013 g/cm^3 (0.036 lb/in^3)	ISO 1183-1
Moisture Rate	< 1 %	ISO-6711
Melt flow index (MFI)	13.6 g/10 min	ISO 1133-1(@190°C-2.16kg)
Melting Temperature (Tm)	149°C (300°F)	ISO 11357-1 DSC (10°C/min- -90-190°C)

Properties	Values	Test Methods
Tensile Modulus	63 MPa (9.1 ksi)	ISO 37/2/500
Tensile Strength	32.8 MPa (4.76 ksi)	ISO 37/2/500
Tensile Strain at Strength	> 550 %	ISO 37/2/500
Tensile Stress at Break	32.3 MPa (4.68 ksi)	ISO 37/2/500
Tensile Strain at Break (type A)	> 550 %	ISO 37/2/500
Flexural Modulus	70 MPa (10 ksi)	ISO 178
Flexural Stress at Conventional Deflection (3.5% Strain)*	2.4 MPa (0.35 ksi)	ISO 178
Charpy Impact Resistance	No Break	ISO 179-1/1eA
Shore Hardness	93 A	ISO 868

PROCESSING

Printing Direction	XY
Printing Speed	44 mm/s
Nozzle Temperature	235°C - 245°C (455°F - 473°F)
Bed Temperature	80°C - 90°C (176°F - 194°F)

NOTES

- *According to ISO 178, end of the test at 5% deformation even if there is no specimen break.
- The data should be considered as indicative values - Properties can be influenced by production conditions.

As the conditions or methods of use, including storage, are beyond our control, Airtech Europe does not assume any responsibility for the performance of this material for any particular use. The material is sold "as is". Airtech Europe disclaims, and buyer waives, any and all implied warranties, including without limitation the implied warranties of merchantability and of fitness for particular use. The information contained herein represents typical properties and should not be used for specification purposes. This translation is provided for your convenience only. The official language is English and the official law is Luxembourg.